



# Maxxam™ 6 T/40 HD White 70

## Polypropylene Homopolymer

### Key Characteristics

#### Product Description

PolyOne's Maxxam™ family of polypropylene- and polyethylene-based products covers a wide range of applications, markets and performance requirements. Standard grades are compounded with calcium carbonate, glass and talc to provide a desired balance of properties including stiffness, durability, impact resistance and heat resistance. Custom grades are available with features such as UV stabilizers, heat stabilizers, custom color, high impact, etc.

#### General

Material Status	• Commercial: Active
Regional Availability	• Europe
Filler / Reinforcement	• Talc, 40% Filler by Weight
Features	• Chemical Resistant • Detergent Resistant • Good Heat Resistance • Good Processability • Good Stiffness • Good Strength • Medium Flow
Uses	• Appliance Components • Automotive Applications • Consumer Applications • General Purpose • Industrial Applications
Appearance	• White
Forms	• Pellets
Processing Method	• Injection Molding

### Technical Properties <sup>1</sup>

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density	1.24 g/cm <sup>3</sup>	1.24 g/cm <sup>3</sup>	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	6.0 g/10 min	6.0 g/10 min	ISO 1133
Mechanical	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Modulus	551000 psi	3800 MPa	ISO 527-2/1
Tensile Stress	4350 psi	30.0 MPa	ISO 527-2/50
Tensile Strain (Yield)	2.5 %	2.5 %	ISO 527-2/50
Impact	Typical Value (English)	Typical Value (SI)	Test Method
Notched Izod Impact Strength	1.2 ft·lb/in <sup>2</sup>	2.5 kJ/m <sup>2</sup>	ISO 180/A
Thermal	Typical Value (English)	Typical Value (SI)	
Melting Temperature	320 to 329 °F	160 to 165 °C	
Flammability	Typical Value (English)	Typical Value (SI)	Test Method
Flame Rating	HB	HB	UL 94

### Processing Information

Injection	Typical Value (English)	Typical Value (SI)
Drying Temperature	176 °F	80 °C
Drying Time	1.0 hr	1.0 hr
Rear Temperature	347 to 365 °F	175 to 185 °C
Middle Temperature	356 to 374 °F	180 to 190 °C
Front Temperature	365 to 383 °F	185 to 195 °C
Nozzle Temperature	374 to 392 °F	190 to 200 °C
Mold Temperature	77 to 131 °F	25 to 55 °C