



Maxxam™ C4 T/25 H-D White 70

Polypropylene Copolymer

Key Characteristics

Product Description

PolyOne's Maxxam™ family of polypropylene- and polyethylene-based products covers a wide range of applications, markets and performance requirements. Standard grades are compounded with calcium carbonate, glass and talc to provide a desired balance of properties including stiffness, durability, impact resistance and heat resistance. Custom grades are available with features such as UV stabilizers, heat stabilizers, custom color, high impact, etc.

General

Material Status	• Commercial: Active		
Regional Availability	• Europe		
Filler / Reinforcement	• Talc, 25% Filler by Weight		
Features	• Chemical Resistant • Detergent Resistant • Good Impact Resistance	• Good Processability • Good Stiffness • Good Strength	• Heat Stabilized • High Heat Resistance • Low Flow
Uses	• Appliances • Automotive Applications	• Consumer Applications • General Purpose	• Industrial Applications
Appearance	• White		
Forms	• Pellets		
Processing Method	• Injection Molding		

Technical Properties ¹

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density	1.07 g/cm ³	1.07 g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	4.0 g/10 min	4.0 g/10 min	ISO 1133
Mechanical	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Modulus	384000 psi	2650 MPa	ISO 527-2/1
Tensile Stress	4350 psi	30.0 MPa	ISO 527-2/50
Tensile Strain (Yield)	4.5 %	4.5 %	ISO 527-2/50
Impact	Typical Value (English)	Typical Value (SI)	Test Method
Notched Izod Impact Strength	2.1 ft-lb/in ²	4.5 kJ/m ²	ISO 180/A
Thermal	Typical Value (English)	Typical Value (SI)	
Melting Temperature	320 to 329 °F	160 to 165 °C	
Flammability	Typical Value (English)	Typical Value (SI)	Test Method
Flame Rating (0.06 in (1.6 mm))	HB	HB	UL 94
Glow Wire Flammability Index	1200 °F	650 °C	IEC 60695-2-12

Processing Information

Injection	Typical Value (English)	Typical Value (SI)
Drying Temperature	176 °F	80 °C
Drying Time	1.0 hr	1.0 hr
Rear Temperature	347 to 365 °F	175 to 185 °C
Middle Temperature	356 to 374 °F	180 to 190 °C
Front Temperature	365 to 383 °F	185 to 195 °C
Nozzle Temperature	383 to 392 °F	195 to 200 °C
Mold Temperature	77 to 131 °F	25 to 55 °C