



Maxxam™ FR H12 T/15 H V2 Orange 70

Polypropylene Homopolymer

Key Characteristics

Product Description

Maxxam™ FR flame-retardant polyolefin compounds and masterbatches meet stringent flammability performance requirements defined by industry agencies, including Underwriters Laboratories UL 94 V-2, performance ratings.

General

Material Status	• Commercial: Active		
Regional Availability	• Europe		
Filler / Reinforcement	• Talc, 15% Filler by Weight		
Features	• Flame Retardant • Good Heat Resistance • Good Processability	• Good Stiffness • Good Strength • Heat Stabilized	• High Flow
Uses	• Consumer Applications • Electrical/Electronic Applications	• General Purpose • Household Goods	• Industrial Applications
RoHS Compliance	• RoHS Compliant		
Appearance	• Orange		
Forms	• Pellets		
Processing Method	• Injection Molding		

Technical Properties ¹

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density	1.05 g/cm ³	1.05 g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	12 g/10 min	12 g/10 min	ISO 1133
Mechanical	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Modulus	326000 psi	2250 MPa	ISO 527-2/1
Tensile Stress	4350 psi	30.0 MPa	ISO 527-2/50
Tensile Strain ² (Yield)	5.0 %	5.0 %	ISO 527-2
Impact	Typical Value (English)	Typical Value (SI)	Test Method
Notched Izod Impact Strength	1.2 ft-lb/in ²	2.5 kJ/m ²	ISO 180/A
Thermal	Typical Value (English)	Typical Value (SI)	Test Method
Melting Temperature	320 to 329 °F	160 to 165 °C	Internal Method
Flammability	Typical Value (English)	Typical Value (SI)	Test Method
Flame Rating (0.06 in (1.6 mm))	V-2	V-2	UL 94
Glow Wire Flammability Index 0.04 to 0.12 in (1.0 to 3.0 mm)	1380 °F	750 °C	IEC 60695-2-12

Processing Information

Injection	Typical Value (English)	Typical Value (SI)
Drying Temperature	176 °F	80 °C
Drying Time	1.0 hr	1.0 hr
Rear Temperature	347 to 365 °F	175 to 185 °C
Middle Temperature	356 to 374 °F	180 to 190 °C
Front Temperature	365 to 383 °F	185 to 195 °C
Nozzle Temperature	374 to 392 °F	190 to 200 °C
Mold Temperature	77 to 131 °F	25 to 55 °C

Notes

¹ Typical values are not to be construed as specifications.

² 2.0 in/min (50 mm/min)



Beyond Polymers.

Better Business Solutions.SM