



Maxxam™ FR PP 301 NATL S-30

Polypropylene

Key Characteristics

Product Description

Maxxam™ FR flame-retardant polyolefin compounds and masterbatches meet stringent flammability performance requirements defined by industry agencies, including Underwriters Laboratories UL 94 V-2, V-0, and 5VA performance ratings. In addition, many compounds in the Maxxam FR portfolio offer elevated Relative Thermal Index (RTI) ratings.

General

Material Status	• Commercial: Active		
Regional Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• Flame Retardant		
Forms	• Pellets		

Technical Properties ¹

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density / Specific Gravity	0.980	0.980	ASTM D792
Melt Mass-Flow Rate (MFR) ² (230°C/2.16 kg)	27 g/10 min	27 g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.010 to 0.020 in/in	1.0 to 2.0 %	ASTM D955
Molding Shrinkage - Across Flow	0.010 to 0.020 in/in	1.0 to 2.0 %	ASTM D955
Mechanical	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Strength ³ (Yield)	4200 psi	29.0 MPa	ASTM D638
Flexural Modulus	175000 psi	1210 MPa	ASTM D790
Impact	Typical Value (English)	Typical Value (SI)	Test Method
Notched Izod Impact 73°F (23°C), 0.125 in (3.18 mm), Injection Molded	0.40 ft·lb/in	21 J/m	ASTM D256A
Thermal	Typical Value (English)	Typical Value (SI)	Test Method
Deflection Temperature Under Load 66 psi (0.45 MPa), Unannealed, 0.125 in (3.18 mm)	185 °F	85.0 °C	ASTM D648
RTI Elec			UL 746
0.016 in (0.41 mm)	212 °F	100 °C	
0.030 in (0.75 mm)	230 °F	110 °C	
0.06 in (1.5 mm)	230 °F	110 °C	
0.12 in (3.0 mm)	230 °F	110 °C	
RTI Imp			UL 746
0.016 in (0.41 mm)	194 °F	90.0 °C	
0.030 in (0.75 mm)	221 °F	105 °C	
0.06 in (1.5 mm)	221 °F	105 °C	
0.12 in (3.0 mm)	239 °F	115 °C	
RTI Str			UL 746
0.016 in (0.41 mm)	212 °F	100 °C	
0.030 in (0.75 mm)	230 °F	110 °C	
0.06 in (1.5 mm)	230 °F	110 °C	
0.12 in (3.0 mm)	248 °F	120 °C	

Flammability	Typical Value (English)	Typical Value (SI)	Test Method
Flame Rating			UL 94
0.030 in (0.75 mm)	V-0	V-0	
0.12 in (3.0 mm)	V-0	V-0	
0.016 in (0.40 mm)	VTM-0	VTM-0	

Notes

¹ Typical values are not to be construed as specifications.

² Procedure A

³ Type I, 2.0 in/min (51 mm/min)



Beyond Polymers.

Better Business Solutions. SM