



Maxxam™ FR PP 401

Polypropylene

Key Characteristics

Product Description

Maxxam™ FR flame-retardant polyolefin compounds and masterbatches meet stringent flammability performance requirements defined by industry agencies, including Underwriters Laboratories UL 94 V-2, V-0, and 5VA performance ratings. In addition, many compounds in the Maxxam FR portfolio offer elevated Relative Thermal Index (RTI) ratings.

General

Material Status	• Commercial: Active		
Regional Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• Flame Retardant	• Medium Flow	
Forms	• Pellets		

Technical Properties ¹

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density / Specific Gravity	0.930	0.930	ASTM D792
Specific Volume	29.9 in ³ /lb	1.08 cm ³ /g	ASTM D792
Melt Mass-Flow Rate (MFR) ² (230°C/2.16 kg)	9.0 g/10 min	9.0 g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.011 to 0.017 in/in	1.1 to 1.7 %	ASTM D955
Mechanical	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Strength ³ (Yield)	4400 psi	30.3 MPa	ASTM D638
Tensile Elongation ³ (Break)	200 %	200 %	ASTM D638
Flexural Modulus	185000 psi	1280 MPa	ASTM D790
Impact	Typical Value (English)	Typical Value (SI)	Test Method
Notched Izod Impact 73°F (23°C), 0.125 in (3.18 mm), Injection Molded	0.70 ft-lb/in	37 J/m	ASTM D256A
Thermal	Typical Value (English)	Typical Value (SI)	Test Method
Deflection Temperature Under Load 66 psi (0.45 MPa), Annealed, 0.125 in (3.18 mm)	205 °F	96.1 °C	ASTM D648
RTI Str	221 °F	105 °C	UL 746
Flammability	Typical Value (English)	Typical Value (SI)	Test Method
Flame Rating (0.028 in (0.70 mm), ALL)	V-2	V-2	UL 94

Notes

¹ Typical values are not to be construed as specifications.

² Procedure A

³ Type I, 2.0 in/min (51 mm/min)