



# Maxxam™ FR PP FR 7B11 BK287

## Polypropylene

### Key Characteristics

#### Product Description

Maxxam™ FR flame-retardant polyolefin compounds and masterbatches meet stringent flammability performance requirements defined by industry agencies, including Underwriters Laboratories UL 94 V-2, V-0, and 5VA performance ratings. In addition, many compounds in the Maxxam FR portfolio offer elevated Relative Thermal Index (RTI) ratings.

#### General

Material Status	• Commercial: Active		
Regional Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• Flame Retardant	• Medium Flow	
Forms	• Pellets		

### Technical Properties <sup>1</sup>

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density / Specific Gravity	0.942	0.942	ASTM D792
Molding Shrinkage - Flow (Injection Molded)	0.010 to 0.020 in/in	1.0 to 2.0 %	ASTM D955
Mechanical	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Strength <sup>2</sup> (Yield)	4060 psi	28.0 MPa	ASTM D638
Flexural Modulus	131000 psi	900 MPa	ASTM D790
Impact	Typical Value (English)	Typical Value (SI)	Test Method
Notched Izod Impact 73°F (23°C), 0.125 in (3.18 mm), Injection Molded	6.6 ft·lb/in	350 J/m	ASTM D256A
Thermal	Typical Value (English)	Typical Value (SI)	Test Method
Deflection Temperature Under Load 66 psi (0.45 MPa), Unannealed, 0.125 in (3.18 mm)	208 °F	98.0 °C	ASTM D648
Flammability	Typical Value (English)	Typical Value (SI)	Test Method
Flame Rating			UL 94
0.031 in (0.79 mm), ALL	V-2	V-2	
0.06 in (1.5 mm)	V-2	V-2	
0.12 in (3.0 mm)	V-2	V-2	

#### Notes

<sup>1</sup> Typical values are not to be construed as specifications.

<sup>2</sup> Type I, 2.0 in/min (51 mm/min)