



# Maxxam™ FR WC 0587-21 R2 RoHS

## Polypropylene

### Key Characteristics

#### Product Description

Maxxam FR WC 0587-21 R2 RoHS is a flame retardant polyolefin compound characterized by low flame spread and good processability. Designed for thin wall primary wire applications.

#### General

Material Status	• Commercial: Active
Regional Availability	• North America
Features	• Flame Retardant
Uses	• Wire & Cable Applications
RoHS Compliance	• RoHS Compliant
Forms	• Pellets
Processing Method	• Extrusion

### Technical Properties <sup>1</sup>

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density / Specific Gravity	1.46	1.46	ASTM D792
Elastomers	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Strength <sup>2, 3</sup> (Break)	2300 psi	15.9 MPa	ASTM D412
Tensile Elongation <sup>2, 3</sup> (Break)	320 %	320 %	ASTM D412
Electrical	Typical Value (English)	Typical Value (SI)	Test Method
Dielectric Constant <sup>4</sup> 0.100 in (2.54 mm), 10 kHz	2.70	2.70	ASTM D150
Flammability	Typical Value (English)	Typical Value (SI)	Test Method
Flame Rating (molded specimen)	V-0	V-0	UL 94
Oxygen Index	34 %	34 %	ASTM D2863

#### Additional Information

UL Yellow Card approval for Plenum cable compounds - Component (E203704)

#### Notes

<sup>1</sup> Typical values are not to be construed as specifications.

<sup>2</sup> 20 in/min (510 mm/min)

<sup>3</sup> Tensile and elongation values are largely determined by processing parameters of the end user.

<sup>4</sup> QuadTech™ Digibridge