



Maxxam™ H6 GF/30 H Black

Polypropylene Homopolymer

Key Characteristics

Product Description

PolyOne's Maxxam™ family of polypropylene- and polyethylene-based products covers a wide range of applications, markets and performance requirements. Standard grades are compounded with calcium carbonate, glass and talc to provide a desired balance of properties including stiffness, durability, impact resistance and heat resistance. Custom grades are available with features such as UV stabilizers, heat stabilizers, custom color, high impact, etc.

General

Material Status	• Commercial: Active		
Regional Availability	• Europe		
Filler / Reinforcement	• Glass Fiber, 30% Filler by Weight		
Additive	• Heat Stabilizer		
Features	• Chemically Coupled • Filled	• General Purpose • Homopolymer	
Uses	• Appliances • Automotive Applications	• Construction Applications • Consumer Applications	• General Purpose • Industrial Applications
RoHS Compliance	• RoHS Compliant		
Appearance	• Black		
Forms	• Pellets		
Processing Method	• Injection Molding		
Resin ID (ISO 1043)	• PP-GF30		

Technical Properties ¹

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density ² (73°F (23°C))	1.13 g/cm ³	1.13 g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	6.0 g/10 min	6.0 g/10 min	ISO 1133
Melt Volume-Flow Rate (MVR) (230°C/2.16 kg)	6.00 cm ³ /10min	6.00 cm ³ /10min	ISO 1133
Molding Shrinkage - Across Flow ³ 73°F (23°C), 0.0787 in (2.00 mm)	0.30 to 0.60 %	0.30 to 0.60 %	ISO 294-4
Mechanical	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Modulus 73°F (23°C), 0.157 in (4.00 mm), Injection Molded	798000 psi	5500 MPa	ISO 527-2/1
Tensile Stress Break, 73°F (23°C), 0.157 in (4.00 mm)	10200 psi	70.0 MPa	ISO 527-2/5
Tensile Strain Break, 73°F (23°C), 0.157 in (4.00 mm)	3.0 %	3.0 %	ISO 527-2/5
Impact	Typical Value (English)	Typical Value (SI)	Test Method
Notched Izod Impact Strength 73°F (23°C), Injection Molded	5.2 ft·lb/in ²	11 kJ/m ²	ISO 180/A
Flammability	Typical Value (English)	Typical Value (SI)	Test Method
Flame Rating (0.06 in (1.6 mm))	HB	HB	UL 94

Notes

¹ Typical values are not to be construed as specifications.

² ±0.03

³ Internal Method



Beyond Polymers.

Better Business Solutions. SM