



Maxxam™ FR PO Conc 62

Low Density Polyethylene

Key Characteristics

Product Description

Maxxam™ FR flame-retardant polyolefin compounds and masterbatches meet stringent flammability performance requirements defined by industry agencies, including Underwriters Laboratories UL 94 V-2, V-0, and 5VA performance ratings. In addition, many compounds in the Maxxam FR portfolio offer elevated Relative Thermal Index (RTI) ratings.

General

Material Status	• Commercial: Active		
Regional Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• Flame Retardant		
Forms	• Pellets		

Technical Properties ¹

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Specific Gravity	1.67	1.67	ASTM D792
Melt Mass-Flow Rate (MFR) ² (190°C/2.16 kg)	2.7 g/10 min	2.7 g/10 min	ASTM D1238

Additional Information

MAXXAM FR PO Concentrate 62 is designated to impart good flame retardancy and UV stability to low and high density polyethylene. Because there are so many varieties of polyethylene, it is difficult to predict the let-down ratio required to meet the specific flammability standards. For starting point formulations we would suggest: 4-7 parts by weight of Low Density Polyethylene-.5 parts by weight of High Density Polyethylene-to 1 part of Concentrate 62. When this concentrate is letdown at the proper ratio the resulting materials can achieve flame retardancy equivalent to the requirements of the UL-94 V-2 or VTM-2. BFD IX-1 and NFPA 701 performance criteria achievable using 8% PO CONC 62 in LDPE film @ 4-8 mil film / V-2 performance criteria achievable in PE @ 15-30% in thickness >= 1.5mm. The effects on the physicals should be minimal.

Notes

¹ Typical values are not to be construed as specifications.

² Procedure A

CONTACT INFORMATION**Americas**

United States - Avon Lake
+1 440 930 1000

United States - McHenry
+1 815 385 8500

Asia

China - Guangzhou
+86 20 8732 7260

China - Shenzhen
+86 755 2969 2888

China - Suzhou
+86 512 6823 24 38

China - Suzhou
+86 512 6265 2600

Hong Kong -
+852 2690 5332

Taiwan - Yonghe City,
+886 9396 99740, +886 2929 1849

Europe

Germany - Gaggenau
+49 7225 6802 0

Spain - Barbastro (Huesca)
+34 974 310 314



Beyond Polymers.

Better Business Solutions. SM

www.polyone.com

PolyOne Americas

33587 Walker Road
Avon Lake, Ohio 44012
United States
+1 440 930 1000
+1 866 POLYONE

PolyOne Asia

No. 88 Guoshoujing Road
Z.J Hi-tech Park, Pudong
Shanghai, 201203, China
+86 21 5080 1188

PolyOne Europe

6 Giällewee
+352 269 050 35

Copyright ©, 2015 PolyOne Corporation. PolyOne makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. PolyOne makes no warranties or guarantees respecting suitability of either PolyOne's products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. POLYONE MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.