



# Maxxam™ MX5200-5004 RS BLACK

## Polypropylene Homopolymer

### Key Characteristics

#### Product Description

PolyOne's Maxxam™ family of polypropylene- and polyethylene-based products covers a wide range of applications, markets and performance requirements. Standard grades are compounded with calcium carbonate, glass and talc to provide a desired balance of properties including stiffness, durability, impact resistance and heat resistance. Custom grades are available with features such as UV stabilizers, heat stabilizers, custom color, high impact, etc.

#### General

Material Status	• Commercial: Active		
Regional Availability	• Africa & Middle East	• Europe	• North America
	• Asia Pacific	• Latin America	
Filler / Reinforcement	• Talc/Mineral		
Features	• General Purpose	• Homopolymer	
Uses	• Automotive Applications	• Consumer Applications	• Industrial Applications
	• Construction Applications	• General Purpose	
Forms	• Pellets		
Processing Method	• Injection Molding		

### Technical Properties <sup>1</sup>

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density / Specific Gravity	1.07	1.07	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	12 g/10 min	12 g/10 min	ISO 1133
Mechanical	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Modulus <sup>2</sup>	383000 psi	2640 MPa	ISO 527
Tensile Stress <sup>3</sup> (Yield)	4370 psi	30.2 MPa	ISO 527
Flexural Modulus <sup>4</sup>	323000 psi	2220 MPa	ISO 178
Impact	Typical Value (English)	Typical Value (SI)	Test Method
Notched Izod Impact Strength			ISO 180
-40°F (-40°C)	1.0 ft·lb/in <sup>2</sup>	2.1 kJ/m <sup>2</sup>	
73°F (23°C)	1.5 ft·lb/in <sup>2</sup>	3.1 kJ/m <sup>2</sup>	
Thermal	Typical Value (English)	Typical Value (SI)	Test Method
Heat Deflection Temperature			ISO 75-2/B
66 psi (0.45 MPa), Unannealed	284 °F	140 °C	
Heat Deflection Temperature			ISO 75-2/A
264 psi (1.8 MPa), Unannealed	201 °F	94.0 °C	
Flammability	Typical Value (English)	Typical Value (SI)	Test Method
Burning Rate	0.85 in/min	22 mm/min	ISO 3795

### Processing Information

Injection	Typical Value (English)	Typical Value (SI)
Drying Temperature	176 °F	80 °C
Drying Time	1.0 hr	1.0 hr
Rear Temperature	365 to 392 °F	185 to 200 °C
Middle Temperature	392 to 419 °F	200 to 215 °C
Front Temperature	401 to 428 °F	205 to 220 °C
Nozzle Temperature	401 to 428 °F	205 to 220 °C

Injection	Typical Value (English)	Typical Value (SI)
Mold Temperature	104 °F	40 °C
Injection Rate	Moderate	Moderate
Back Pressure	1160 psi	8.00 MPa

**Notes**

<sup>1</sup> Typical values are not to be construed as specifications.

<sup>2</sup> 0.039 in/min (1 mm/min)

<sup>3</sup> 2.0 in/min (50 mm/min)

<sup>4</sup> 0.079 in/min (2.0 mm/min)



*Beyond Polymers.*

*Better Business Solutions. <sup>SM</sup>*