



Maxxam™ PP5120N B1

Polypropylene Homopolymer

Key Characteristics

Product Description

PolyOne's Maxxam™ family of polypropylene- and polyethylene-based products covers a wide range of applications, markets and performance requirements. Standard grades are compounded with calcium carbonate, glass and talc to provide a desired balance of properties including stiffness, durability, impact resistance and heat resistance. Custom grades are available with features such as UV stabilizers, heat stabilizers, custom color, high impact, etc.

General

Material Status	• Commercial: Active
Regional Availability	• Africa & Middle East • Asia Pacific • Europe • Latin America • North America
Filler / Reinforcement	• Talc\Mineral, 22% Filler by Weight
Features	• General Purpose • Homopolymer
Uses	• Automotive Applications • Construction Applications • Consumer Applications • General Purpose • Industrial Applications
Appearance	• Black
Forms	• Pellets
Processing Method	• Injection Molding

Technical Properties ¹

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density / Specific Gravity	1.05	1.05	ISO 1183
Mechanical	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Stress (Yield)	4350 psi	30.0 MPa	ISO 527-2
Flexural Modulus	363000 psi	2500 MPa	ISO 178
Impact	Typical Value (English)	Typical Value (SI)	Test Method
Charpy Unnotched Impact Strength	9.5 ft·lb/in ²	20 kJ/m ²	ISO 179
Notched Izod Impact Strength (73°F (23°C))	1.2 ft·lb/in ²	2.5 kJ/m ²	ISO 180
Thermal	Typical Value (English)	Typical Value (SI)	Test Method
Heat Deflection Temperature 264 psi (1.8 MPa), Unannealed	142 °F	61.0 °C	ISO 75-2/A

Notes

¹ Typical values are not to be construed as specifications.