



Nymax™ 600 A HS Natural A

Polyamide 6 Alloy

Key Characteristics

Product Description

The Nymax® 600 Blend Series of nylon 6 materials are "salt-and-pepper" pelletized blends combining select nylon resins and process aids, performance modifiers, and color concentrates. These materials have been formulated to provide improved melt processing, part performance, or surface appearance depending upon grade selected and are offered as an economical alternative to fully compounded products.

General

Material Status	• Commercial: Active		
Regional Availability	• Latin America	• North America	
Additive	• Heat Stabilizer		
Features	• General Purpose	• Heat Stabilized	
Uses	• Automotive Applications • Construction Applications	• Consumer Applications • General Purpose	• Industrial Applications
Automotive Specifications	• GM GMP.PA6.008 Color: Black	• GM GMP.PA6.008 Color: Natural	
Appearance	• Natural Color		
Forms	• Pellets		
Processing Method	• Injection Molding		

Technical Properties ¹

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density / Specific Gravity	1.14	1.14	ASTM D792
Molding Shrinkage - Flow	0.012 in/in	1.2 %	ASTM D955
Water Absorption (24 hr, 0.125 in (3.18 mm))	1.7 %	1.7 %	ASTM D570
Mechanical	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Strength ² (Break)	11300 psi	77.9 MPa	ASTM D638
Tensile Elongation ² (Break)	95 %	95 %	ASTM D638
Flexural Modulus	385000 psi	2650 MPa	ASTM D790
Flexural Strength	16000 psi	110 MPa	ASTM D790
Impact	Typical Value (English)	Typical Value (SI)	Test Method
Notched Izod Impact 73°F (23°C), 0.125 in (3.18 mm), Injection Molded	1.2 ft·lb/in	64 J/m	ASTM D256A
Thermal	Typical Value (English)	Typical Value (SI)	Test Method
Deflection Temperature Under Load 66 psi (0.45 MPa), Unannealed, 0.125 in (3.18 mm)	329 °F	165 °C	ASTM D648
Deflection Temperature Under Load 264 psi (1.8 MPa), Unannealed, 0.125 in (3.18 mm)	145 °F	63.0 °C	ASTM D648
Melting Temperature	419 °F	215 °C	ASTM D789
Additional Information			
Molded Test Bars: Dry as Molded			

Processing Information

Injection	Typical Value (English)	Typical Value (SI)
Drying Temperature	180 °F	82 °C
Drying Time	4.0 hr	4.0 hr
Mold Temperature	120 to 200 °F	49 to 93 °C

Notes

¹ Typical values are not to be construed as specifications.

² Type I, 0.20 in/min (5.1 mm/min)