



Versollan™ OM 1255NX-1

Thermoplastic Elastomer

Key Characteristics

Product Description

Versollan™ OM 1255NX-1 is a high performance TPU alloy designed for thin-wall overmolding onto polycarbonate (PC), ABS, PC/ABS and copolyester substrates.

- Improved Grip with Matte, Rubbery Finish
- Superior Adhesion to PC, ABS, PC/ABS, PC/PBT and Copolyester

General

Material Status	• Commercial: Active		
Regional Availability	• Africa & Middle East • Asia Pacific	• Latin America • North America	
Features	• Good Colorability • Good Moldability	• Good Processability • Low Gloss	
Uses	• Business Equipment • Consumer Applications • Electrical/Electronic Applications	• Flexible Grips • Overmolding • Power/Other Tools	• Thin-walled Parts
Agency Ratings	• UL 94		
RoHS Compliance	• RoHS Compliant		
Appearance	• Natural Color		
Forms	• Pellets		
Processing Method	• Injection Molding		

Technical Properties ¹

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Specific Gravity	1.05	1.05	ASTM D792
Melt Mass-Flow Rate (MFR)			ASTM D1238
190°C/2.16 kg	8.0 g/10 min	8.0 g/10 min	
200°C/5.0 kg	130 g/10 min	130 g/10 min	
Molding Shrinkage - Flow	7.0E-3 to 0.013 in/in	0.70 to 1.3 %	ASTM D955
Elastomers	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Stress ^{2, 3} (100% Strain, 73°F (23°C))	280 psi	1.93 MPa	ASTM D412
Tensile Stress ^{2, 3} (300% Strain, 73°F (23°C))	492 psi	3.39 MPa	ASTM D412
Tensile Strength ^{2, 3} (Break, 73°F (23°C))	955 psi	6.58 MPa	ASTM D412
Tensile Elongation ^{2, 3} (Break, 73°F (23°C))	650 %	650 %	ASTM D412
Tear Strength	220 lbf/in	38.5 kN/m	ASTM D624
Compression Set (73°F (23°C), 22 hr)	26 %	26 %	ASTM D395B
Hardness	Typical Value (English)	Typical Value (SI)	Test Method
Durometer Hardness (Shore A, 10 sec)	59	59	ASTM D2240
Thermal	Typical Value (English)	Typical Value (SI)	Test Method
Brittleness Temperature ⁴	-91.3 °F	-68.5 °C	ASTM D746
Flammability	Typical Value (English)	Typical Value (SI)	Test Method
Flame Rating (0.06 in (1.5 mm))	HB	HB	UL 94

Copyright © 2016 PolyOne Corporation. PolyOne makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. PolyOne makes no warranties or guarantees respecting suitability of either PolyOne's products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. POLYONE MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.

Fill Analysis	Typical Value (English)	Typical Value (SI)	Test Method
Apparent Viscosity			ASTM D3835
392°F (200°C), 11200 sec ⁻¹	16.7 Pa·s	16.7 Pa·s	

Processing Information

Injection	Typical Value (English)	Typical Value (SI)
Drying Temperature	125 to 130 °F	51.7 to 54.4 °C
Drying Time	3.0 to 4.0 hr	3.0 to 4.0 hr
Suggested Max Moisture	< 0.030 %	< 0.030 %
Suggested Max Regrind	20 %	20 %
Rear Temperature	325 to 365 °F	163 to 185 °C
Middle Temperature	335 to 385 °F	168 to 196 °C
Front Temperature	350 to 410 °F	177 to 210 °C
Nozzle Temperature	350 to 410 °F	177 to 210 °C
Mold Temperature	70.0 to 120 °F	21.1 to 48.9 °C
Back Pressure	25.0 to 50.0 psi	0.172 to 0.345 MPa
Screw Speed	75 to 125 rpm	75 to 125 rpm

Injection Notes

Color concentrates with polyether or polyester-based urethane carriers are most suitable for coloring Versollan™ OM 1255NX-1. Typical letdown ratios are 50:1 to 25:1 - loading levels should be as low as possible to minimize the effect on hardness. A high color match consistency can be obtained by the use of precolored compounds available from GLS. Polypropylene (PP) based color concentrates are not recommended because they significantly affect adhesion of the TPE to the substrate. Concentrates based on TPE should not be used. The final determination of color concentrate suitability should be determined by customer trials.

Purge thoroughly before and after use of this product with a low flow (0.5 - 2.5 MFR) polyethylene (PE) or polypropylene (PP).

Regrind levels up to 20% can be used with Versollan™ OM 1255NX-1 with minimal property loss, provided that the regrind is free of contamination. To minimize losses during molding, the melt temperature should remain as low as possible. The final determination of regrind effectiveness should be determined by the customer.

Versollan™ OM 1255NX-1 should not be left in the barrel for extended idle periods (greater than 5 minutes).

Suggested Dewpoint: -40°F

Injection Speed: 1 to 5 in/sec
 1st Stage - Boost Pressure: 200 to 800 psi
 2nd Stage - Hold Pressure: 70% of Boost
 Hold Time (Thick Part): 4 to 10 sec
 Hold Time (Thin Part): 1 to 3 sec

Notes

¹ Typical values are not to be construed as specifications.

² Die C

³ 2 hr

⁴ Thickness = 1.90mm
 Conditioned for 40hrs at 23C at 50% RH

CONTACT INFORMATION**Americas**

United States - Avon Lake
+1 440 930 1000

United States - McHenry
+1 815 385 8500

Asia

China - Guangzhou
+86 20 8732 7260

China - Shenzhen
+86 755 2969 2888

China - Suzhou
+86 512 6823 24 38

China - Suzhou
+86 512 6265 2600

Hong Kong -
+852 2690 5332

Taiwan - Yonghe City,
+886 9396 99740, +886 2929 1849

Europe

Germany - Gaggenau
+49 7225 6802 0

Spain - Barbastro (Huesca)
+34 974 310 314



Beyond Polymers.

Better Business Solutions. SM

www.polyone.com

PolyOne Americas

33587 Walker Road
Avon Lake, Ohio 44012
United States
+1 440 930 1000
+1 866 POLYONE

PolyOne Asia

No. 88 Guoshoujing Road
Z.J Hi-tech Park, Pudong
Shanghai, 201203, China
+86 21 5080 1188

PolyOne Europe

6 Giällewee
+352 269 050 35

Copyright ©, 2016 PolyOne Corporation. PolyOne makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. PolyOne makes no warranties or guarantees respecting suitability of either PolyOne's products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. POLYONE MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.