

Versaflex™ OM 9-801N

Thermoplastic Elastomer

Key Characteristics

Product Description

Versaflex™ OM 9-801N is designed for overmolding onto a wide variety of substrates including PC, ABS, PC/ABS, HIPS, PPO, acetal, acrylic and copolyester.

- Bonds to a Variety Of Substrates
- Rubbery Feel
- Soft Touch
- Very Good Surface Aesthetics

General

Material Status	• Commercial: Active		
Regional Availability	• Africa & Middle East • Asia Pacific	• Latin America • North America	
Features	• Good Surface Finish		
Uses	• Flexible Grips • General Purpose	• Overmolding • Soft Touch Applications	• Sporting Goods
Agency Ratings	• FDA Unspecified Rating	• UL 94	
RoHS Compliance	• RoHS Compliant		
Automotive Specifications	• FMVSS 302		
Appearance	• Natural Color		
Forms	• Pellets		
Processing Method	• Injection Molding		

Technical Properties ¹

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density / Specific Gravity	1.04	1.04	ASTM D792
Melt Mass-Flow Rate (MFR)			ASTM D1238
190°C/2.16 kg	22 g/10 min	22 g/10 min	
200°C/5.0 kg	100 g/10 min	100 g/10 min	
Molding Shrinkage - Flow	3.0E-3 to 9.0E-3 in/in	0.30 to 0.90 %	ASTM D955
Elastomers	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Stress ^{2,3} (100% Strain, 73°F (23°C))	210 psi	1.45 MPa	ASTM D412
Tensile Stress ^{2,3} (300% Strain, 73°F (23°C))	261 psi	1.80 MPa	ASTM D412
Tensile Strength ^{2,3} (Break, 73°F (23°C))	651 psi	4.49 MPa	ASTM D412
Tensile Elongation ^{2,3} (Break, 73°F (23°C))	820 %	820 %	ASTM D412
Tear Strength	100 lbf/in	17.5 kN/m	ASTM D624
Compression Set (73°F (23°C), 22 hr)	43 %	43 %	ASTM D395B
Hardness	Typical Value (English)	Typical Value (SI)	Test Method
Durometer Hardness (Shore A, 10 sec)	47	47	ASTM D2240
Flammability	Typical Value (English)	Typical Value (SI)	Test Method
Flame Rating (0.06 in (1.5 mm))	HB	HB	UL 94
Fill Analysis	Typical Value (English)	Typical Value (SI)	Test Method
Apparent Viscosity			ASTM D3835
392°F (200°C), 11200 sec ⁻¹	15.6 Pa·s	15.6 Pa·s	

Copyright © 2021 Avient Corporation. Avient makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. Avient makes no warranties or guarantees respecting suitability of either Avient's products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. Avient MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.

Processing Information

Injection	Typical Value (English)	Typical Value (SI)
Suggested Max Regrind	20 %	20 %
Rear Temperature	360 to 380 °F	182 to 193 °C
Middle Temperature	370 to 395 °F	188 to 202 °C
Front Temperature	380 to 400 °F	193 to 204 °C
Nozzle Temperature	390 to 425 °F	199 to 218 °C
Mold Temperature	70 to 100 °F	21 to 38 °C
Back Pressure	25.0 to 50.0 psi	0.172 to 0.345 MPa
Screw Speed	75 to 125 rpm	75 to 125 rpm

Injection Notes

Color concentrates with polyethylene (PE) or EVA carriers are most suitable for coloring Versaflex™ OM 9-801N. Typical letdown ratios are 50:1 to 25:1 - loading levels should be as low as possible to minimize the effect on adhesion. A high color match consistency can be obtained by the use of precolored compounds available from GLS. Concentrates based on PVC should not be used. The final determination of color concentrate suitability should be determined by customer trials.

Purge thoroughly before and after use of this product with a low flow (0.5 - 2.5 MFR) polystyrene (PS) or polypropylene (PP).

Regrind levels up to 20% can be used with Versaflex™ OM 9-801N with minimal property loss, provided that the regrind is free of contamination. To minimize losses during molding, the melt temperature should remain as low as possible. The final determination of regrind effectiveness should be determined by the customer.

Versaflex™ OM 9-801N has good melt stability. Maximum residence times may vary, depending on the size of the barrel. Generally, the barrel should be emptied if it is idle for periods of 5 - 8 minutes or longer.

Drying is not Required

Injection Speed: 0.5 to 3 in/sec
 1st Stage - Boost Pressure: 500 to 900 psi
 2nd Stage - Hold Pressure: 70% of Boost
 Hold Time (Thick Part): 4 to 10 sec
 Hold Time (Thin Part): 1 to 3 sec

Notes

¹ Typical values are not to be construed as specifications.

² Die C

³ 2 hr

CONTACT INFORMATION

North America

Avon Lake, United States
 33587 Walker Road
 Avon Lake, OH, United States ,
 44012
 +1 440 930 1000
 +1 844 4AVIENT

South America

Sao Paulo, Brazil
 Av. Francisco Nakasato, 1700
 13295-000 Itupeva
 Sao Paulo, Brazil
 +55 11 4593 9200

Asia

Shanghai, China
 2F, Block C
 200 Jinsu Road
 Pudong, 201206
 Shanghai, China
 +86 (0) 21 6028 4888

Europe

Pommerloch, Luxembourg
 19 Route de Bastogne
 Pommerloch, Luxembourg , L-9638
 +352 269 050 35



avient.com

Copyright © 2021 Avient Corporation. Avient makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. Avient makes no warranties or guarantees respecting suitability of either Avient's products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. Avient MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.