



# OnFlex™ S 30A-3E2618

## Thermoplastic Elastomer

### Key Characteristics

#### Product Description

OnFlex™-S thermoplastic elastomer compounds are based on hydrogenated styrenic block copolymers. OnFlex S 30A-3E2618 is formulated to have low odour and fogging, and is stabilized for metal contact.

#### General

|                       |  |                             |                 |
|-----------------------|--|-----------------------------|-----------------|
| Material Status       | • Commercial: Active                     |                             |                 |
| Regional Availability | • Africa & Middle East<br>• Asia Pacific | • Europe<br>• Latin America | • North America |
| Features              | • Copper Contact Stabilized              | • Low Fogging               | • Low Odor      |
| Uses                  | • Automotive Applications                | • Automotive Interior Parts |                 |
| RoHS Compliance       | • RoHS Compliant                         |                             |                 |
| Forms                 | • Pellets                                |                             |                 |
| Processing Method     | • Injection Molding                      |                             |                 |

### Technical Properties <sup>1</sup>

| Physical   | Typical Value (English)                      | Typical Value (SI)                           | Test Method |
|--|--|--|-------------|
| Density  | 0.990 g/cm <sup>3</sup>                      | 0.990 g/cm <sup>3</sup>                      | ISO 1183    |
| Elastomers   | Typical Value (English)                      | Typical Value (SI)                           | Test Method |
| Tensile Stress <sup>2</sup>                              |  |  | DIN 53504   |
| Across Flow : Break, 73°F (23°C),<br>0.0787 in (2.00 mm) | 914 psi                                      | 6.30 MPa                                     |             |
| Flow : Break, 73°F (23°C), 0.0787 in<br>(2.00 mm)        | 392 psi                                      | 2.70 MPa                                     |             |
| Tensile Elongation <sup>2</sup>                          |  |  | DIN 53504   |
| Across Flow : Break, 73°F (23°C),<br>0.0787 in (2.00 mm) | 810 %  | 810 %  |             |
| Flow : Break, 73°F (23°C), 0.0787 in<br>(2.00 mm)        | 610 %  | 610 %  |             |
| Compression Set (158°F (70°C), 22 hr)                    | 29 %   | 29 %   | ISO 815     |
| Hardness   | Typical Value (English)                      | Typical Value (SI)                           | Test Method |
| Shore Hardness (Shore A)                                 | 30   | 30   | ISO 868     |
| Flammability   | Typical Value (English)                      | Typical Value (SI)                           | Test Method |
| Flame Spread   | 70 mm/min                                    | 70 mm/min                                    | FMVSS 302   |
| Fogging <sup>3</sup>                                     | 0.85 mg                                      | 0.85 mg                                      | DIN 75201   |
| Additional Information                                   | Typical Value (English)                      | Typical Value (SI)                           | Test Method |
| Generic Material Type                                    | Styrenic<br>Thermoplastic<br>Elastomer (TES) | Styrenic<br>Thermoplastic<br>Elastomer (TES) |             |
| Odor Rating <sup>4</sup>                                 | 3.0  | 3.0  | VDA 270     |

Properties are measured using injection molded plaques.

### Processing Information

| Injection              | Typical Value (English) | Typical Value (SI) |
|------------------------|-------------------------|--------------------|
| Processing (Melt) Temp | 356 to 428 °F           | 180 to 220 °C      |
| Mold Temperature       | 86 to 140 °F            | 30 to 60 °C        |
| Injection Rate         | Fast                    | Fast               |

| Injection     | Typical Value (English) | Typical Value (SI) |
|---------------|-------------------------|--------------------|
| Back Pressure | > 3.00 psi              | > 0.0207 MPa       |

**Notes**

<sup>1</sup> Typical values are not to be construed as specifications.

<sup>2</sup> 7.9 in/min (200 mm/min)

<sup>3</sup> Method B

<sup>4</sup> Method A3



*Beyond Polymers.*

*Better Business Solutions. SM*