



# OnFlex™ S HF 60A-3S1982

## Thermoplastic Elastomer

### Key Characteristics

#### Product Description

OnFlex™-S HF thermoplastic elastomer compounds are based on hydrogenated styrenic block copolymers. This range of compounds utilize a unique, patent pending halogen free flame retardancy system. Furthermore, OnFlex™-S HF compounds offer good mechanical properties, compliance with UL94 V-0, good LOI values, wide hardness range, good processability, and excellent UV stability.

#### General

Material Status	• Commercial: Active		
Regional Availability	• Africa & Middle East	• Europe	• Latin America
Features	• Flame Retardant		
Uses	• Automotive Applications	• Electrical/Electronic Applications	• Industrial Applications
	• Business Equipment	• General Purpose	
RoHS Compliance	• RoHS Compliant		
Forms	• Pellets		
Processing Method	• Injection Molding		

### Technical Properties <sup>1</sup>

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density	1.09 g/cm <sup>3</sup>	1.09 g/cm <sup>3</sup>	ISO 1183
Elastomers	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Stress (100% Strain)	247 psi	1.70 MPa	ISO 37
Tensile Stress (300% Strain)	363 psi	2.50 MPa	ISO 37
Tensile Stress (Break)	435 psi	3.00 MPa	ISO 37
Tensile Elongation (Break)	400 %	400 %	ISO 37
Tear Strength	120 lbf/in	21.0 kN/m	ISO 34-1
Compression Set			ISO 815
73°F (23°C), 72 hr	17 %	17 %	
158°F (70°C), 22 hr	47 %	47 %	
212°F (100°C), 22 hr	82 %	82 %	
Hardness	Typical Value (English)	Typical Value (SI)	Test Method
Shore Hardness (Shore A)	60	60	ISO 868
Electrical	Typical Value (English)	Typical Value (SI)	Test Method
Comparative Tracking Index	550 V	550 V	IEC 60112
Flammability	Typical Value (English)	Typical Value (SI)	Test Method
Flame Rating (0.06 in (1.5 mm))	V-0	V-0	UL 94
Glow Wire Flammability Index			IEC 60695-2-12
0.08 in (2.0 mm)	1760 °F	960 °C	
Glow Wire Ignition Temperature			IEC 60695-2-13
0.08 in (2.0 mm)	1340 °F	725 °C	
Oxygen Index	37 %	37 %	ISO 4589-2
Additional Information	Typical Value (English)	Typical Value (SI)	
Generic Material Type	Styrenic Thermoplastic Elastomer (TES)	Styrenic Thermoplastic Elastomer (TES)	

Properties are measured using injection molded plaques.

**Processing Information**

Injection	Typical Value (English)	Typical Value (SI)
Drying Temperature	176 °F	80 °C
Drying Time	2.0 hr	2.0 hr
Processing (Melt) Temp	320 to 356 °F	160 to 180 °C
Mold Temperature	86 to 122 °F	30 to 50 °C
Injection Rate	Moderate-Fast	Moderate-Fast

**Notes**

<sup>1</sup> Typical values are not to be construed as specifications.



*Beyond Polymers.*

*Better Business Solutions. SM*