



OnFlex™ BIO 5370A-E0004

Thermoplastic Elastomer

Key Characteristics

Product Description

OnFlex™-Bio 5300 series thermoplastic elastomer compounds are soft thermoplastic polyurethane compounds made from renewable natural sources. These compounds contain at least 20% of renewable material as certified according to ASTM-D6866. The OnFlex™-Bio 5300 series compounds are formulated to provide an excellent surface finish, soft-touch haptic, abrasion resistance and mechanical properties.

General

Material Status	• Commercial: Active		
Regional Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• Good Abrasion Resistance	• Renewable Resource Content	• Scratch Resistant
Uses	• Automotive Applications	• Consumer Applications	• General Purpose
RoHS Compliance	• RoHS Compliant		
Forms	• Pellets		
Processing Method	• Calendering • Extrusion	• Injection Molding • Multi Injection Molding	

Technical Properties ¹

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density	1.05 g/cm ³	1.05 g/cm ³	ISO 1183
Mechanical	Typical Value (English)	Typical Value (SI)	Test Method
Abrasion Loss	63.0 mm ³	63.0 mm ³	DIN 53516
Elastomers	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Stress ²			DIN 53504
Across Flow : 100% Strain, 73°F (23°C), 0.0787 in (2.00 mm)	479 psi	3.30 MPa	
Flow : 100% Strain, 73°F (23°C), 0.0787 in (2.00 mm)	551 psi	3.80 MPa	
Tensile Stress ²			DIN 53504
Across Flow : 300% Strain, 73°F (23°C), 0.0787 in (2.00 mm)	1150 psi	7.90 MPa	
Flow : 300% Strain, 73°F (23°C), 0.0787 in (2.00 mm)	1330 psi	9.20 MPa	
Tensile Stress ²			DIN 53504
Across Flow : Break, 73°F (23°C), 0.0787 in (2.00 mm)	1600 psi	11.0 MPa	
Flow : Break, 73°F (23°C), 0.0787 in (2.00 mm)	1840 psi	12.7 MPa	
Tensile Elongation ²			DIN 53504
Across Flow : Break, 73°F (23°C), 0.0787 in (2.00 mm)	410 %	410 %	
Flow : Break, 73°F (23°C), 0.0787 in (2.00 mm)	410 %	410 %	
Tear Strength ³			ISO 34-1
Across Flow : 73°F (23°C), 0.0787 in (2.00 mm)	240 lbf/in	43 kN/m	
Flow : 73°F (23°C), 0.0787 in (2.00 mm)	270 lbf/in	47 kN/m	

Copyright ©, 2015 PolyOne Corporation. PolyOne makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. PolyOne makes no warranties or guarantees respecting suitability of either PolyOne's products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. POLYONE MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.

Elastomers	Typical Value (English)	Typical Value (SI)	Test Method
Compression Set			ISO 815
73°F (23°C), 72 hr	51 %	51 %	
158°F (70°C), 22 hr	73 %	73 %	
212°F (100°C), 22 hr	84 %	84 %	
Hardness	Typical Value (English)	Typical Value (SI)	Test Method
Shore Hardness (Shore A)	70	70	ISO 868
Additional Information	Typical Value (English)	Typical Value (SI)	Test Method
Odor Rating ⁴	3.0	3.0	VDA 270

Properties are measured using injection molded plaques.

Processing Information

Injection	Typical Value (English)	Typical Value (SI)
Drying Temperature	212 to 248 °F	100 to 120 °C
Drying Time	1.0 to 2.0 hr	1.0 to 2.0 hr
Processing (Melt) Temp	356 to 428 °F	180 to 220 °C
Mold Temperature	86.0 to 140 °F	30.0 to 60.0 °C
Injection Rate	Fast	Fast

Notes

¹ Typical values are not to be construed as specifications.

² Type 1, 7.9 in/min (200 mm/min)

³ Method A, Trouser

⁴ Method A3

CONTACT INFORMATION

Americas

United States - Avon Lake
+1 440 930 1000

United States - McHenry
+1 815 385 8500

Asia

China - Guangzhou
+86 20 8732 7260

China - Shenzhen
+86 755 2969 2888

China - Suzhou
+86 512 6823 24 38

China - Suzhou
+86 512 6265 2600

Hong Kong -
+852 2690 5332

Taiwan - Yonghe City,
+886 9396 99740, +886 2929 1849

Europe

Germany - Gaggenau
+49 7225 6802 0

Spain - Barbastro (Huesca)
+34 974 310 314



Beyond Polymers.

Better Business Solutions. SM

www.polyone.com

PolyOne Americas

33587 Walker Road
Avon Lake, Ohio 44012
United States
+1 440 930 1000
+1 866 POLYONE

PolyOne Asia

No. 88 Guoshoujing Road
Z.J Hi-tech Park, Pudong
Shanghai, 201203, China
+86 21 5080 1188

PolyOne Europe

6 Giallewee
+352 269 050 35

Copyright ©, 2015 PolyOne Corporation. PolyOne makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. PolyOne makes no warranties or guarantees respecting suitability of either PolyOne's products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. POLYONE MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.