



OnFlex™ HT 60A-3S2101

Thermoplastic Elastomer

Key Characteristics

Product Description

OnFlex™ HT thermoplastic elastomer compounds are based on hydrogenated styrenic block copolymers. This range of compounds is specially formulated to deliver very good compression set performance at elevated temperatures and a high heat resistance. Furthermore, OnFlex™ HT compounds are in compliance with EN 681-2 and offer excellent mechanical properties, a wide hardness range and good processability.

General

Material Status	• Commercial: Active		
Regional Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• High Heat Resistance	• Low Compression Set	• Ozone Resistant
Uses	• Pipe Seals		
RoHS Compliance	• RoHS Compliant		
Forms	• Pellets		
Processing Method	• Extrusion	• Injection Molding	

Technical Properties ¹

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density	1.00 g/cm ³	1.00 g/cm ³	ISO 1183
Elastomers	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Stress ²			DIN 53504
Across Flow : Break, 73°F (23°C), 0.0787 in (2.00 mm)	1520 psi	10.5 MPa	
Flow : Break, 73°F (23°C), 0.0787 in (2.00 mm)	1150 psi	7.90 MPa	
Tensile Elongation ²			DIN 53504
Across Flow : Break, 73°F (23°C), 0.0787 in (2.00 mm)	840 %	840 %	
Flow : Break, 73°F (23°C), 0.0787 in (2.00 mm)	650 %	650 %	
Tear Strength	180 lbf/in	32 kN/m	ISO 34-1
Compression Set			ISO 815
14°F (-10°C), 72 hr	46 %	46 %	
73°F (23°C), 22 hr	24 %	24 %	
158°F (70°C), 22 hr	33 %	33 %	
212°F (100°C), 22 hr	42 %	42 %	
257°F (125°C), 22 hr	43 %	43 %	
302°F (150°C), 22 hr	65 %	65 %	
Stress Relaxation			ISO 3384
73°F (23°C) ³	31 %	31 %	
73°F (23°C) ⁴	13 %	13 %	
Hardness	Typical Value (English)	Typical Value (SI)	Test Method
Shore Hardness			DIN 53505
Shore A, 3 sec, 73°F (23°C), 0.236 in (6.00 mm), Injection Molded	60	60	
IRHD Hardness	70	70	ISO 48

Copyright © 2015 PolyOne Corporation. PolyOne makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. PolyOne makes no warranties or guarantees respecting suitability of either PolyOne's products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. POLYONE MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.

Aging	Typical Value (English)	Typical Value (SI)	Test Method
Change in Tensile Strength in Air 158°F (70°C), 168 hr, 0.0787 in (2.00 mm)	-0.50 %	-0.50 %	DIN 53504
Change in Tensile Strain at Break in Air 158°F (70°C), 168 hr, 0.0787 in (2.00 mm)	-0.90 %	-0.90 %	DIN 53504
Change in Shore Hardness in Air Shore A, 158°F (70°C), 168 hr	-3.0	-3.0	DIN 53505
Change in Volume 158°F (70°C), 72 hr, in ASTM #1 Oil 158°F (70°C), 168 hr, in Water	10 % 0.20 %	10 % 0.20 %	ISO 1817
Additional Information	Typical Value (English)	Typical Value (SI)	
Generic Material Type	Styrenic Thermoplastic Elastomer (TES)	Styrenic Thermoplastic Elastomer (TES)	
Properties are measured using injection molded plaques.			

Processing Information

Injection	Typical Value (English)	Typical Value (SI)
Processing (Melt) Temp	356 to 428 °F	180 to 220 °C
Mold Temperature	86.0 to 140 °F	30.0 to 60.0 °C
Injection Rate	Fast	Fast

Notes

¹ Typical values are not to be construed as specifications.

² 7.9 in/min (200 mm/min)

³ 100d, 25% compression, Method A

⁴ 168hrs, 25% compression, Method A

CONTACT INFORMATION

Americas

United States - Avon Lake
+1 440 930 1000

United States - McHenry
+1 815 385 8500

Asia

China - Guangzhou
+86 20 8732 7260

China - Shenzhen
+86 755 2969 2888

China - Suzhou
+86 512 6823 24 38

China - Suzhou
+86 512 6265 2600

Hong Kong -
+852 2690 5332

Taiwan - Yonghe City,
+886 9396 99740, +886 2929 1849

Europe

Germany - Gaggenau
+49 7225 6802 0

Spain - Barbastro (Huesca)
+34 974 310 314



Beyond Polymers.

Better Business Solutions. SM

www.polyone.com

PolyOne Americas

33587 Walker Road
Avon Lake, Ohio 44012
United States
+1 440 930 1000
+1 866 POLYONE

PolyOne Asia

No. 88 Guoshoujing Road
Z.J Hi-tech Park, Pudong
Shanghai, 201203, China
+86 21 5080 1188

PolyOne Europe

6 Giällewee
+352 269 050 35

Copyright ©, 2015 PolyOne Corporation. PolyOne makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. PolyOne makes no warranties or guarantees respecting suitability of either PolyOne's products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. POLYONE MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.