



OnFlex™ U 5470A-E0083

Thermoplastic Elastomer

Key Characteristics

Product Description			
OnFlex™-U thermoplastic elastomer compounds are based on thermoplastic polyurethane elastomers (TPE-U). The OnFlex™-U 5400 series are based upon alloys of SEBS and aliphatic TPU, combining the advantages of both raw materials, for example the good processability and soft haptic of a TPE-S with the excellent mechanical properties and abrasion resistance of a TPE-U. OnFlex™-U 5400 compounds are formulated to deliver very good scratch resistance, a wide hardness range, good chemical resistance, and good light stability.			
General			
Material Status	• Commercial: Active		
Regional Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• Good Abrasion Resistance • Good UV Resistance	• Oil Resistant • Scratch Resistant	
Uses	• Automotive Applications • Consumer Applications	• General Purpose • Industrial Applications	• Power/Other Tools
RoHS Compliance	• RoHS Compliant		
Appearance	• Matte Finish		
Forms	• Pellets		
Processing Method	• Calendering	• Film Extrusion	• Injection Molding

Technical Properties ¹

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density	1.08 g/cm ³	1.08 g/cm ³	ISO 1183
Mechanical	Typical Value (English)	Typical Value (SI)	Test Method
Abrasion Loss	35.0 mm ³	35.0 mm ³	DIN 53516
Elastomers	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Stress ²			ISO 37
Across Flow : Break, 73°F (23°C), 0.0787 in (2.00 mm)	3080 psi	21.3 MPa	
Flow : Break, 73°F (23°C), 0.0787 in (2.00 mm)	3210 psi	22.2 MPa	
Tensile Elongation ²			ISO 37
Across Flow : Break, 73°F (23°C), 0.0787 in (2.00 mm)	480 %	480 %	
Flow : Break, 73°F (23°C), 0.0787 in (2.00 mm)	490 %	490 %	
Tear Strength ³			ISO 34-1
Across Flow : 73°F (23°C), 0.0787 in (2.00 mm)	320 lbf/in	56 kN/m	
Flow : 73°F (23°C), 0.0787 in (2.00 mm)	340 lbf/in	59 kN/m	
Hardness	Typical Value (English)	Typical Value (SI)	Test Method
Shore Hardness (Shore A)	70	70	ISO 868
Flammability	Typical Value (English)	Typical Value (SI)	Test Method
Fogging (212°F (100°C))	1.1 mg	1.1 mg	DIN 75201B

Copyright © 2015 PolyOne Corporation. PolyOne makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. PolyOne makes no warranties or guarantees respecting suitability of either PolyOne's products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. POLYONE MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.

Additional Information	Typical Value (English)	Typical Value (SI)	Test Method
Generic Material Type	Thermoplastic Polyurethane Elastomer Alloy (TPU Alloy)	Thermoplastic Polyurethane Elastomer Alloy (TPU Alloy)	
Odor Rating	2.30	2.30	VDA 270
Properties are measured using injection molded plaques.			

Processing Information

Injection	Typical Value (English)	Typical Value (SI)
Drying Temperature	212 °F	100 °C
Drying Time	2.0 hr	2.0 hr
Processing (Melt) Temp	320 to 392 °F	160 to 200 °C
Mold Temperature	86.0 to 140 °F	30.0 to 60.0 °C
Injection Rate	Slow	Slow

Notes

¹ Typical values are not to be construed as specifications.

² Type 2, 7.9 in/min (200 mm/min)

³ Method A, Trouser, 20 in/min (500 mm/min)

CONTACT INFORMATION

Americas

United States - Avon Lake
+1 440 930 1000

United States - McHenry
+1 815 385 8500

Asia

China - Guangzhou
+86 20 8732 7260

China - Shenzhen
+86 755 2969 2888

China - Suzhou
+86 512 6823 24 38

China - Suzhou
+86 512 6265 2600

Hong Kong -
+852 2690 5332

Taiwan - Yonghe City,
+886 9396 99740, +886 2929 1849

Europe

Germany - Gaggenau
+49 7225 6802 0

Spain - Barbastró (Huesca)
+34 974 310 314



Beyond Polymers.

Better Business Solutions. SM

www.polyone.com

PolyOne Americas

33587 Walker Road
Avon Lake, Ohio 44012
United States
+1 440 930 1000
+1 866 POLYONE

PolyOne Asia

No. 88 Guoshoujing Road
Z.J Hi-tech Park, Pudong
Shanghai, 201203, China
+86 21 5080 1188

PolyOne Europe

6 Giällewee
+352 269 050 35

Copyright ©, 2015 PolyOne Corporation. PolyOne makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. PolyOne makes no warranties or guarantees respecting suitability of either PolyOne's products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. POLYONE MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.