



OnForce™ LFT LF5200-5007 BLACK UV

Polypropylene Homopolymer

Key Characteristics

Product Description

PolyOne's Long Fiber Thermoplastic (LFT) compounds are formulated for demanding applications which require high stiffness and good impact such as metal replacement or other structural applications. These products exhibit enhanced physical and mechanical properties versus standard short fiber products. Benefits of LFT compounds include improved impact strength, elastic modulus, and material strength across wide temperature ranges from subambient to highly elevated. Furthermore, LFT compounds have been shown to offer improved performance in the areas of creep and fatigue performance, improved dimensional stability, and exhibit an exceptional surface finish when compared to traditional highly filled short fiber products.

General

Material Status	• Commercial: Active
Regional Availability	• Africa & Middle East • Europe • Asia Pacific • Latin America • North America
Filler / Reinforcement	• Long Glass Fiber
Features	• UV Resistant
Forms	• Pellets

Technical Properties ¹

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density	1.34 g/cm ³	1.34 g/cm ³	ISO 1183
Mechanical	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Modulus	1.65E+6 psi	11400 MPa	ISO 527-2
Tensile Stress (Break)	17400 psi	120 MPa	ISO 527-2
Tensile Strain (Break)	1.5 %	1.5 %	ISO 527-2
Flexural Modulus	1.39E+6 psi	9600 MPa	ISO 178
Flexural Stress	27600 psi	190 MPa	ISO 178
Impact	Typical Value (English)	Typical Value (SI)	Test Method
Charpy Notched Impact Strength	9.0 ft·lb/in ²	19 kJ/m ²	ISO 179
Charpy Unnotched Impact Strength	25 ft·lb/in ²	52 kJ/m ²	ISO 179
Notched Izod Impact Strength	8.6 ft·lb/in ²	18 kJ/m ²	ISO 180
Thermal	Typical Value (English)	Typical Value (SI)	Test Method
Heat Deflection Temperature 264 psi (1.8 MPa), Unannealed	309 °F	154 °C	ISO 75-2/A
Heat Deflection Temperature 1160 psi (8.0 MPa), Unannealed	282 °F	139 °C	ISO 75-2/C

Processing Information

Injection	Typical Value (English)	Typical Value (SI)
Drying Temperature	176 °F	80 °C
Drying Time	2.0 hr	2.0 hr
Processing (Melt) Temp	410 to 446 °F	210 to 230 °C
Mold Temperature	140 to 176 °F	60 to 80 °C
Injection Rate	Slow-Moderate	Slow-Moderate
Back Pressure	725 psi	5.00 MPa

Injection Notes

LFT compounds can be processed using equipments similar to those used for short fiber products. The mechanical properties depend greatly on the length of the fibers in the moulded part; therefore processing conditions must be set carefully in order to minimize fiber breakage. A "low shear process" is advised, with low back pressure, low screw speed and low to medium injection speed.

Notes

¹ Typical values are not to be construed as specifications.



Beyond Polymers.

Better Business Solutions.™