



OnForce™ LFT PP-60LGF/001 Black UV

Polypropylene Homopolymer

Key Characteristics

Product Description

PolyOne's Long Fiber Thermoplastic (LFT) compounds are formulated for demanding applications which require high stiffness and good impact such as metal replacement or other structural applications. These products exhibit enhanced physical and mechanical properties versus standard short fiber products. Benefits of LFT compounds include improved impact strength, elastic modulus, and material strength across wide temperature ranges from subambient to highly elevated. Furthermore, LFT compounds have been shown to offer improved performance in the areas of creep and fatigue performance, improved dimensional stability, and exhibit an exceptional surface finish when compared to traditional highly filled short fiber products.

General

Material Status	• Commercial: Active
Regional Availability	• Africa & Middle East • Europe • Asia Pacific • Latin America • North America
Filler / Reinforcement	• Long Glass Fiber, 60% Filler by Weight
Uses	• Automotive Applications • Industrial Applications • Metal Replacement
RoHS Compliance	• RoHS Compliant
Forms	• Pellets

Technical Properties ¹

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density	1.40 g/cm ³	1.40 g/cm ³	ISO 1183
Molding Shrinkage	0.10 to 0.30 %	0.10 to 0.30 %	ISO 294-4
Mechanical	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Modulus	2.18E+6 psi	15000 MPa	ISO 527-2
Tensile Stress (Break)	18900 psi	130 MPa	ISO 527-2
Tensile Strain (Break)	1.0 to 1.5 %	1.0 to 1.5 %	ISO 527-2
Flexural Modulus	1.67E+6 psi	11500 MPa	ISO 178
Flexural Stress	26100 psi	180 MPa	ISO 178
Impact	Typical Value (English)	Typical Value (SI)	Test Method
Charpy Notched Impact Strength	9.5 ft·lb/in ²	20 kJ/m ²	ISO 179
Charpy Unnotched Impact Strength	26 ft·lb/in ²	55 kJ/m ²	ISO 179
Thermal	Typical Value (English)	Typical Value (SI)	Test Method
Heat Deflection Temperature 264 psi (1.8 MPa), Unannealed	311 °F	155 °C	ISO 75-2/A

Processing Information

Injection	Typical Value (English)	Typical Value (SI)
Drying Temperature	176 °F	80 °C
Drying Time	2.0 hr	2.0 hr
Processing (Melt) Temp	410 to 446 °F	210 to 230 °C
Mold Temperature	140 °F	60 °C
Injection Rate	Slow-Moderate	Slow-Moderate
Back Pressure	145 psi	1.00 MPa

Notes

¹ Typical values are not to be construed as specifications.