



# Maxxam™ PD 20 TF Black

## Polypropylene

### Key Characteristics

#### Product Description

PolyOne's Maxxam™ family of polypropylene- and polyethylene-based products covers a wide range of applications, markets and performance requirements. Standard grades are compounded with calcium carbonate, glass and talc to provide a desired balance of properties including stiffness, durability, impact resistance and heat resistance. Custom grades are available with features such as UV stabilizers, heat stabilizers, custom color, high impact, etc.

#### General

Material Status	• Commercial: Active
Regional Availability	• Africa & Middle East • Asia Pacific • Europe • Latin America • North America
Filler / Reinforcement	• Talc, 23% Filler by Weight
Features	• Medium Flow
Appearance	• Black
Forms	• Pellets

### Technical Properties <sup>1</sup>

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Specific Gravity	1.07	1.07	ASTM D792
Melt Mass-Flow Rate (MFR) <sup>2</sup> (230°C/2.16 kg)	17 g/10 min	17 g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.011 to 0.012 in/in	1.1 to 1.2 %	ASTM D955
Mechanical	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Strength <sup>3</sup> (Yield)	4700 psi	32.4 MPa	ASTM D638
Tensile Elongation <sup>3</sup> (Break)	44 %	44 %	ASTM D638
Flexural Modulus	350000 psi	2410 MPa	ASTM D790
Impact	Typical Value (English)	Typical Value (SI)	Test Method
Notched Izod Impact 73°F (23°C), 0.125 in (3.18 mm), Injection Molded	0.50 ft-lb/in	27 J/m	ASTM D256A
Thermal	Typical Value (English)	Typical Value (SI)	Test Method
Deflection Temperature Under Load 66 psi (0.45 MPa), Unannealed, 0.125 in (3.18 mm)	252 °F	122 °C	ASTM D648
Deflection Temperature Under Load 264 psi (1.8 MPa), Annealed, 0.125 in (3.18 mm)	155 °F	68.5 °C	ASTM D648
Flammability	Typical Value (English)	Typical Value (SI)	Test Method
Flame Rating (0.06 in (1.5 mm), BK)	HB	HB	UL 94

### Processing Information

Injection	Typical Value (English)	Typical Value (SI)
Mold Temperature	60.8 to 122 °F	16.0 to 50.0 °C