



Edgetek™ AS/018 White

Acrylonitrile Butadiene Styrene

Key Characteristics

Product Description

The Edgetek® Engineering Thermoplastic Compounds portfolio covers a broad range of standard and custom-formulated high performance materials. This portfolio includes high-temperature materials for elevated service temperature environments, high-modulus / structural materials for load-bearing and high-strength applications and flame-retardant products. These compounds are based on select engineering thermoplastic resins that are compounded with reinforcing additives such as carbon fiber, glass fiber and glass beads.

General

Material Status	• Commercial: Active		
Regional Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• Amorphous	• Good Moldability	• Good Toughness
Uses	• Appliances • Automotive Applications	• Consumer Applications • General Purpose	• Industrial Applications • Structural Parts
RoHS Compliance	• RoHS Compliant		
Forms	• Pellets		

Technical Properties ¹

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Specific Gravity	1.21	1.21	ASTM D792
Mechanical	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Strength ² (Yield)	5800 psi	40.0 MPa	ASTM D638
Tensile Elongation ³ (Break)	2.0 to 3.0 %	2.0 to 3.0 %	ASTM D638
Flexural Modulus ⁴	390000 psi	2690 MPa	ASTM D790
Flexural Strength ⁴	10000 psi	68.9 MPa	ASTM D790
Impact	Typical Value (English)	Typical Value (SI)	Test Method
Notched Izod Impact	3.0 ft·lb/in	160 J/m	ASTM D256

Notes

¹ Typical values are not to be construed as specifications.

² 2.0 in/min (51 mm/min)

³ Type I

⁴ 0.50 in/min (13 mm/min)

Copyright © 2015 PolyOne Corporation. PolyOne makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. PolyOne makes no warranties or guarantees respecting suitability of either PolyOne's products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. POLYONE MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.

CONTACT INFORMATION**Americas**

Mexico - Toluca
+52 722 2790200
United States - Avon Lake
+1 440 930 1000

Asia

China - Shanghai
+86 21 5080 1188
China - Shenzhen
+86 755 2969 2888
China - Suzhou
+86 512 6823 24 38
China - Tianjin
+86 22 2532 8818
India - Pune
Japan - Tokyo
+81-3-6261-3980
Singapore - Singapore
+65 6861 9325
Taiwan - Yonghe City,
+886 9396 99740, +886 2929 1849

Europe

Germany - Gaggenau
+49 7225 6802 0
Spain - Barbastro (Huesca)
+34 974 310 314
Turkey - Esenyurt - Istanbul – Turkey
+90 212 549 2256



Beyond Polymers.

Better Business Solutions.™

www.polyone.com

PolyOne Americas

33587 Walker Road
Avon Lake, Ohio 44012
United States
+1 440 930 1000
+1 866 POLYONE

PolyOne Asia

No. 88 Guoshoujing Road
Z.J Hi-tech Park, Pudong
Shanghai, 201203, China
+86 21 5080 1188

PolyOne Europe

6 Giallewee
+352 269 050 35

Copyright ©, 2015 PolyOne Corporation. PolyOne makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. PolyOne makes no warranties or guarantees respecting suitability of either PolyOne's products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. POLYONE MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.