



Edgetek™ TR2-30GF/000 NATURAL Copolyester

Key Characteristics

Product Description

The Edgetek™ engineering thermoplastics compounds made with Eastman Tritan™ copolyester offer a wide range of performance and properties with the addition of reinforcing additives. By utilizing Eastman Tritan™ copolyester these compounds provide chemical resistance, clarity, heat resistance and BPA-free solutions.

General

Material Status	• Commercial: Active		
Regional Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Filler / Reinforcement	• Glass Fiber		
Features	• BPA Free • Chemical Resistant • Crack Resistant	• Crazing Resistant • Filled • Good Dimensional Stability	• Good Toughness • Medium Clarity • Medium Heat Resistance
Uses	• Appliance Components • Consumer Applications	• Food Service Applications • Household Goods	• Industrial Applications • Transparent or Translucent Parts
Forms	• Pellets		

Technical Properties ¹

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density / Specific Gravity	1.41	1.41	ASTM D792
Molding Shrinkage - Flow (0.125 in (3.18 mm))	1.0E-4 to 9.0E-4 in/in	0.010 to 0.090 %	ASTM D955
Mechanical	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Modulus ²	960000 psi	6620 MPa	ASTM D638
Tensile Strength ³ (Yield)	13000 psi	89.6 MPa	ASTM D638
Tensile Strength ² (Break)	13000 psi	89.6 MPa	ASTM D638
Tensile Elongation ³ (Yield)	3.0 %	3.0 %	ASTM D638
Tensile Elongation ² (Break)	3.0 %	3.0 %	ASTM D638
Flexural Modulus ⁴	880000 psi	6070 MPa	ASTM D790
Flexural Strength ⁴	20000 psi	138 MPa	ASTM D790
Impact	Typical Value (English)	Typical Value (SI)	Test Method
Notched Izod Impact 73°F (23°C), 0.125 in (3.18 mm), Injection Molded	2.0 ft·lb/in	110 J/m	ASTM D256A
Unnotched Izod Impact 73°F (23°C), 0.125 in (3.18 mm), Injection Molded	14 ft·lb/in	750 J/m	ASTM D256
Thermal	Typical Value (English)	Typical Value (SI)	Test Method
Deflection Temperature Under Load 66 psi (0.45 MPa), Unannealed, 0.125 in (3.18 mm)	243 °F	117 °C	ASTM D648
Deflection Temperature Under Load 264 psi (1.8 MPa), Unannealed, 0.125 in (3.18 mm)	235 °F	113 °C	ASTM D648
CLTE - Flow (-22 to 86°F (-30 to 30°C))	3.2E-5 in/in/°F	5.8E-5 cm/cm/°C	ASTM E831

Copyright © 2019 PolyOne Corporation. PolyOne makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. PolyOne makes no warranties or guarantees respecting suitability of either PolyOne's products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. POLYONE MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.

Thermal	Typical Value (English)	Typical Value (SI)	Test Method
CLTE - Transverse (-22 to 86°F (-30 to 30°C))	1.0E-4 in/in/°F	1.8E-4 cm/cm/°C	ASTM E831

Processing Information

Injection	Typical Value (English)	Typical Value (SI)
Drying Temperature	190 °F	88 °C
Drying Time	4.0 hr	4.0 hr
Processing (Melt) Temp	510 to 540 °F	266 to 282 °C
Mold Temperature	140 to 150 °F	60 to 66 °C

Notes

¹ Typical values are not to be construed as specifications.

² Type I, 0.20 in/min (5.1 mm/min)

³ 0.20 in/min (5.1 mm/min)

⁴ 0.050 in/min (1.3 mm/min)

CONTACT INFORMATION

Americas

United States - Avon Lake
+1 440 930 1000

United States - McHenry
+1 815 385 8500

Asia

China - Guangzhou
+86 20 8732 7260

China - Shenzhen
+86 755 2969 2888

China - Suzhou
+86 512 6823 24 38

China - Suzhou
+86 512 6265 2600

Hong Kong -
+852 2690 5332

Taiwan - Yonghe City,
+886 9396 99740, +886 2929 1849

Europe

Germany - Gaggenau
+49 7225 6802 0

Spain - Barbastro (Huesca)
+34 974 310 314



Beyond Polymers.

Better Business Solutions.™

www.polyone.com

PolyOne Americas

33587 Walker Road
Avon Lake, Ohio 44012
United States
+1 440 930 1000
+1 866 POLYONE

PolyOne Asia

No. 88 Guoshoujing Road
Z.J Hi-tech Park, Pudong
Shanghai, 201203, China
+86 21 5080 1188

PolyOne Europe

6 Giällewee
+352 269 050 35

Copyright ©, 2019 PolyOne Corporation. PolyOne makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. PolyOne makes no warranties or guarantees respecting suitability of either PolyOne's products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. POLYONE MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.