



Trilliant™ HC HC6200-5002 XR Grey

Polyamide 12

Key Characteristics

Product Description

The Trilliant® specialty compounds offer a complete system of specialty engineered materials, certified processes, services and technical support that enable healthcare OEM's to get to market ahead of competition. When specified, Trilliant® compound may incorporate agency rated materials that meet USP Class IV, FDA or ISO 10993 testing requirements.

This Trilliant® grade is a high density specialty compound featuring a sustainable material solution for radiation shielding and weighting & balancing applications. The composite material offers a high performance thermoplastic-based alternative to lead. This compound has densities similar to traditional metals and provides greater flexibility in design and processing.

General

Material Status	• Commercial: Active		
Regional Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• High Specific Gravity • Medium Impact Resistance • Non-Toxic		
Uses	• Housings • Medical/Healthcare Applications	• Radiation Shielding • Weighting & Balancing	
Appearance	• Grey		
Forms	• Pellets		
Processing Method	• Injection Molding		

Technical Properties ¹

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density	8.00 g/cm ³	8.00 g/cm ³	ISO 1183
Molding Shrinkage	0.60 to 1.1 %	0.60 to 1.1 %	ISO 294-4
Mechanical	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Modulus	783000 psi	5400 MPa	ISO 527-2/1
Tensile Stress (Break)	4640 psi	32.0 MPa	ISO 527-2/50
Tensile Strain (Yield)	0.80 to 2.0 %	0.80 to 2.0 %	ISO 527-2
Tensile Strain (Break)	> 10 %	> 10 %	ISO 527-2/50
Impact	Typical Value (English)	Typical Value (SI)	Test Method
Charpy Notched Impact Strength	2.4 ft·lb/in ²	5.0 kJ/m ²	ISO 179
Charpy Unnotched Impact Strength	4.8 ft·lb/in ²	10 kJ/m ²	ISO 179
Thermal	Typical Value (English)	Typical Value (SI)	Test Method
Heat Deflection Temperature 66 psi (0.45 MPa), Unannealed	302 °F	150 °C	ISO 75-2/B
Heat Deflection Temperature 264 psi (1.8 MPa), Unannealed	230 °F	110 °C	ISO 75-2/A
Thermal Conductivity	10 to 14 Btu·in/hr/ft ² /°F	1.5 to 2.0 W/m/K	ASTM E1461
Electrical	Typical Value (English)	Typical Value (SI)	Test Method
Surface Resistivity	< 1.0E+3 ohms	< 1.0E+3 ohms	IEC 60093

Additional Information

Shielding properties:
 Attenuation coefficient at 511 keV = 0.72cm-1
 Half Thickness at 511 keV = 0.96cm

Copyright © 2019 PolyOne Corporation. PolyOne makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. PolyOne makes no warranties or guarantees respecting suitability of either PolyOne's products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. POLYONE MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.

Processing Information

Injection	Typical Value (English)	Typical Value (SI)
Drying Temperature	176 °F	80 °C
Drying Time	4.0 hr	4.0 hr
Processing (Melt) Temp	446 to 536 °F	230 to 280 °C
Mold Temperature	149 to 212 °F	65 to 100 °C

Notes

¹ Typical values are not to be construed as specifications.

CONTACT INFORMATION

Americas

United States - Avon Lake
+1 440 930 1000

United States - McHenry
+1 815 385 8500

Asia

China - Guangzhou
+86 20 8732 7260

China - Shenzhen
+86 755 2969 2888

China - Suzhou
+86 512 6823 24 38

China - Suzhou
+86 512 6265 2600

Hong Kong -
+852 2690 5332

Taiwan - Yonghe City,
+886 9396 99740, +886 2929 1849

Europe

Germany - Gaggenau
+49 7225 6802 0

Spain - Barbastro (Huesca)
+34 974 310 314



Beyond Polymers.

Better Business Solutions. SM

www.polyone.com

PolyOne Americas

33587 Walker Road
Avon Lake, Ohio 44012
United States
+1 440 930 1000
+1 866 POLYONE

PolyOne Asia

No. 88 Guoshoujing Road
Z.J Hi-tech Park, Pudong
Shanghai, 201203, China
+86 21 5080 1188

PolyOne Europe

6 Giällewee
+352 269 050 35

Copyright ©, 2019 PolyOne Corporation. PolyOne makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. PolyOne makes no warranties or guarantees respecting suitability of either PolyOne's products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. POLYONE MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.