



Bergamid™ B70 G40 Natural 70

Polyamide 6

Key Characteristics

Product Description	
Heat resistant	
General	
Material Status	• Commercial: Active
Regional Availability	• Europe
Filler / Reinforcement	• Glass Fiber, 40% Filler by Weight
Features	• Good Processability • Good Strength • Good Stiffness • High Impact Resistance
Uses	• Automotive Applications • General Purpose • Consumer Applications • Industrial Applications
Appearance	• Natural Color
Forms	• Pellets
Processing Method	• Injection Molding

Technical Properties ¹

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density	1.45 g/cm ³	1.45 g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (235°C/2.16 kg)	2.0 g/10 min	2.0 g/10 min	ISO 1133
Melt Volume-Flow Rate (MVR) (235°C/2.16 kg)	2.00 cm ³ /10min	2.00 cm ³ /10min	ISO 1133
Mechanical	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Modulus	1.60E+6 psi	11000 MPa	ISO 527-2/1
Tensile Stress (Yield)	26100 psi	180 MPa	ISO 527-2/5
Tensile Strain (Break)	3.5 %	3.5 %	ISO 527-2/5
Impact	Typical Value (English)	Typical Value (SI)	Test Method
Notched Izod Impact Strength	9.0 ft-lb/in ²	19 kJ/m ²	ISO 180/A
Thermal	Typical Value (English)	Typical Value (SI)	
Melting Temperature	428 to 437 °F	220 to 225 °C	
Flammability	Typical Value (English)	Typical Value (SI)	Test Method
Flame Rating (0.06 in (1.6 mm))	HB	HB	UL 94

Processing Information

Injection	Typical Value (English)	Typical Value (SI)
Drying Temperature	176 °F	80 °C
Drying Time	2.0 to 4.0 hr	2.0 to 4.0 hr
Rear Temperature	446 to 464 °F	230 to 240 °C
Middle Temperature	455 to 473 °F	235 to 245 °C
Front Temperature	464 to 482 °F	240 to 250 °C
Nozzle Temperature	482 to 500 °F	250 to 260 °C
Mold Temperature	176 °F	80 °C

Notes

¹ Typical values are not to be construed as specifications.

Copyright © 2019 PolyOne Corporation. PolyOne makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. PolyOne makes no warranties or guarantees respecting suitability of either PolyOne's products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. POLYONE MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.

CONTACT INFORMATION

Americas

United States - Avon Lake
+1 440 930 1000

United States - McHenry
+1 815 385 8500

Asia

China - Guangzhou
+86 20 8732 7260

China - Shenzhen
+86 755 2969 2888

China - Suzhou
+86 512 6823 24 38

China - Suzhou
+86 512 6265 2600

Hong Kong -
+852 2690 5332

Taiwan - Yonghe City,
+886 9396 99740, +886 2929 1849

Europe

Germany - Gaggenau
+49 7225 6802 0

Spain - Barbastro (Huesca)
+34 974 310 314



Beyond Polymers.

Better Business Solutions.™

www.polyone.com

PolyOne Americas

33587 Walker Road
Avon Lake, Ohio 44012
United States
+1 440 930 1000
+1 866 POLYONE

PolyOne Asia

No. 88 Guoshoujing Road
Z.J Hi-tech Park, Pudong
Shanghai, 201203, China
+86 21 5080 1188

PolyOne Europe

6 Giällewee
+352 269 050 35

Copyright ©, 2019 PolyOne Corporation. PolyOne makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. PolyOne makes no warranties or guarantees respecting suitability of either PolyOne's products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. POLYONE MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.