



Bergamid™ B70 GK20 UV

Polyamide 6

Key Characteristics

Product Description	
PA6 + Glass Bead	
General	
Material Status	• Commercial: Active
Regional Availability	• Europe
Filler / Reinforcement	• Glass Bead, 20% Filler by Weight
Features	• Good Dimensional Stability • UV Stabilized
RoHS Compliance	• RoHS Compliant
Forms	• Pellets
Processing Method	• Injection Molding

Technical Properties ¹

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density / Specific Gravity ²	1.28	1.28	ISO 1183
Mechanical	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Modulus			ISO 527-2/1
73°F (23°C), 0.157 in (4.00 mm), Injection Molded	551000 psi	3800 MPa	
Tensile Strength ³			ISO 527
73°F (23°C), 0.157 in (4.00 mm), Injection Molded	9430 psi	65.0 MPa	
Tensile Strain			ISO 527-2/5
Break, 73°F (23°C), 0.157 in (4.00 mm), Injection Molded	4.5 %	4.5 %	
Impact	Typical Value (English)	Typical Value (SI)	Test Method
Charpy Notched Impact Strength (73°F (23°C))	1.4 ft·lb/in ²	3.0 kJ/m ²	ISO 179
Charpy Unnotched Impact Strength			ISO 179
73°F (23°C), Injection Molded	24 ft·lb/in ²	50 kJ/m ²	
Thermal	Typical Value (English)	Typical Value (SI)	Test Method
Heat Deflection Temperature			ISO 75-2/B
66 psi (0.45 MPa), Unannealed	356 °F	180 °C	
Heat Deflection Temperature			ISO 75-2/A
264 psi (1.8 MPa), Unannealed	194 °F	90.0 °C	
Flammability	Typical Value (English)	Typical Value (SI)	Test Method
Flame Rating (0.12 in (3.0 mm), ALL)	HB	HB	Internal Method

Processing Information

Injection	Typical Value (English)	Typical Value (SI)
Drying Temperature	176 °F	80 °C
Drying Time	4.0 hr	4.0 hr
Suggested Max Moisture	0.10 %	0.10 %
Processing (Melt) Temp	464 to 536 °F	240 to 280 °C
Mold Temperature	140 to 194 °F	60 to 90 °C

Copyright © 2019 PolyOne Corporation. PolyOne makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. PolyOne makes no warranties or guarantees respecting suitability of either PolyOne's products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. POLYONE MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.

Notes

¹ Typical values are not to be construed as specifications.

² ±0.03

³ 0.20 in/min (5.0 mm/min)

CONTACT INFORMATION

Americas

United States - Avon Lake
+1 440 930 1000

United States - McHenry
+1 815 385 8500

Asia

China - Guangzhou
+86 20 8732 7260

China - Shenzhen
+86 755 2969 2888

China - Suzhou
+86 512 6823 24 38

China - Suzhou
+86 512 6265 2600

Hong Kong -
+852 2690 5332

Taiwan - Yonghe City,
+886 9396 99740, +886 2929 1849

Europe

Germany - Gaggenau
+49 7225 6802 0

Spain - Barbastro (Huesca)
+34 974 310 314



Beyond Polymers.

Better Business Solutions.™

www.polyone.com

PolyOne Americas

33587 Walker Road
Avon Lake, Ohio 44012
United States
+1 440 930 1000
+1 866 POLYONE

PolyOne Asia

No. 88 Guoshoujing Road
Z.J Hi-tech Park, Pudong
Shanghai, 201203, China
+86 21 5080 1188

PolyOne Europe

6 Giällewee
+352 269 050 35

Copyright ©, 2019 PolyOne Corporation. PolyOne makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. PolyOne makes no warranties or guarantees respecting suitability of either PolyOne's products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. POLYONE MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.