



Bergamid™ B70 G/GK30 H BLACK

Polyamide 6

Key Characteristics

Product Description

Bergamid B70 G/GK30 H Black is a Polyamide 6 (Nylon 6) product filled with 30% glass fiber + glass beads. It can be processed by injection molding and is heat stabilized.

General

Material Status	• Commercial: Active
Regional Availability	• Europe
Filler / Reinforcement	• Glass Bead\Glass Fiber, 30% Filler by Weight
Features	• Heat Stabilized
Appearance	• Black
Forms	• Pellets
Processing Method	• Injection Molding

Technical Properties ¹

Physical	Dry	Conditioned	Unit	Test Method
Density ²	1.35	1.35	g/cm ³	ISO 1183
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	943000 (6500)	943000 (6500)	psi (MPa)	ISO 527-2
Tensile Stress	16000 (110)	16000 (110)	psi (MPa)	ISO 527-2
Tensile Strain (Break)	3.0	3.0	%	ISO 527
Flexural Stress	26100 (180)	26100 (180)	psi (MPa)	ISO 178
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength (73°F (23°C))	2.9 (6.0)	2.9 (6.0)	ft·lb/in ² (kJ/m ²)	ISO 179
Charpy Unnotched Impact Strength 73°F (23°C)	19 (40)	19 (40)	ft·lb/in ² (kJ/m ²)	ISO 179
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature 66 psi (0.45 MPa), Unannealed	410 (210)	410 (210)	°F (°C)	ISO 75-2/B
Heat Deflection Temperature 264 psi (1.8 MPa), Unannealed	374 (190)	374 (190)	°F (°C)	ISO 75-2/A
Melting Temperature (DSC)	419 to 437 (215 to 225)	419 to 437 (215 to 225)	°F (°C)	ISO 3146
Electrical	Dry	Conditioned	Unit	Test Method
Comparative Tracking Index	500	500	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating (0.13 in (3.2 mm))	HB	HB		UL 94

Copyright © 2019 PolyOne Corporation. PolyOne makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. PolyOne makes no warranties or guarantees respecting suitability of either PolyOne's products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. POLYONE MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.

Processing Information

Injection	Dry (English)	Dry (SI)
Drying Temperature	176 °F	80 °C
Drying Time	3.0 to 4.0 hr	3.0 to 4.0 hr
Processing (Melt) Temp	500 to 554 °F	260 to 290 °C
Mold Temperature	122 to 194 °F	50 to 90 °C
Holding Pressure	7250 to 14500 psi	50.0 to 100 MPa

Notes

¹ Typical values are not to be construed as specifications.

² +/-0.02

CONTACT INFORMATION

Americas

United States - Avon Lake
+1 440 930 1000

United States - McHenry
+1 815 385 8500

Asia

China - Guangzhou
+86 20 8732 7260

China - Shenzhen
+86 755 2969 2888

China - Suzhou
+86 512 6823 24 38

China - Suzhou
+86 512 6265 2600

Hong Kong -
+852 2690 5332

Taiwan - Yonghe City,
+886 9396 99740, +886 2929 1849

Europe

Germany - Gaggenau
+49 7225 6802 0

Spain - Barbastro (Huesca)
+34 974 310 314



Beyond Polymers.

Better Business Solutions. SM

www.polyone.com

PolyOne Americas

33587 Walker Road
Avon Lake, Ohio 44012
United States
+1 440 930 1000
+1 866 POLYONE

PolyOne Asia

No. 88 Guoshoujing Road
Z.J Hi-tech Park, Pudong
Shanghai, 201203, China
+86 21 5080 1188

PolyOne Europe

6 Giällewee
+352 269 050 35