



Bergamid™ B70 MI10 Black T 70

Polyamide 6

Key Characteristics

General			
Material Status	• Commercial: Active		
Regional Availability	• Europe		
Filler / Reinforcement	• Mineral, 10% Filler by Weight		
Features	• Good Impact Resistance • Good Processability	• Good Stiffness • Good Strength	• Medium Viscosity
Uses	• Appliances • Automotive Applications	• Consumer Applications • Electrical/Electronic Applications	• General Purpose • Industrial Applications
Appearance	• Black		
Forms	• Pellets		
Processing Method	• Injection Molding		

Technical Properties ¹

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density	1.19 g/cm ³	1.19 g/cm ³	ISO 1183
Mechanical	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Modulus	566000 psi	3900 MPa	ISO 527-2/1
Tensile Stress	10900 psi	75.0 MPa	ISO 527-2/50
Tensile Strain (Yield)	4.0 %	4.0 %	ISO 527-2/50
Impact	Typical Value (English)	Typical Value (SI)	Test Method
Notched Izod Impact Strength	2.1 ft-lb/in ²	4.5 kJ/m ²	ISO 180/A
Thermal	Typical Value (English)	Typical Value (SI)	
Melting Temperature	428 to 437 °F	220 to 225 °C	

Processing Information

Injection	Typical Value (English)	Typical Value (SI)
Drying Temperature	176 to 194 °F	80 to 90 °C
Drying Time	2.0 to 4.0 hr	2.0 to 4.0 hr
Rear Temperature	455 to 473 °F	235 to 245 °C
Middle Temperature	464 to 482 °F	240 to 250 °C
Front Temperature	473 to 491 °F	245 to 255 °C
Nozzle Temperature	482 to 500 °F	250 to 260 °C
Mold Temperature	176 °F	80 °C

Notes

¹ Typical values are not to be construed as specifications.

Copyright © 2019 PolyOne Corporation. PolyOne makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. PolyOne makes no warranties or guarantees respecting suitability of either PolyOne's products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. POLYONE MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.

CONTACT INFORMATION

Americas

United States - Avon Lake
+1 440 930 1000

United States - McHenry
+1 815 385 8500

Asia

China - Guangzhou
+86 20 8732 7260

China - Shenzhen
+86 755 2969 2888

China - Suzhou
+86 512 6823 24 38

China - Suzhou
+86 512 6265 2600

Hong Kong -
+852 2690 5332

Taiwan - Yonghe City,
+886 9396 99740, +886 2929 1849

Europe

Germany - Gaggenau
+49 7225 6802 0

Spain - Barbastro (Huesca)
+34 974 310 314



Beyond Polymers.

Better Business Solutions. SM

www.polyone.com

PolyOne Americas

33587 Walker Road
Avon Lake, Ohio 44012
United States
+1 440 930 1000
+1 866 POLYONE

PolyOne Asia

No. 88 Guoshoujing Road
Z.J Hi-tech Park, Pudong
Shanghai, 201203, China
+86 21 5080 1188

PolyOne Europe

6 Giällewee
+352 269 050 35

Copyright ©, 2019 PolyOne Corporation. PolyOne makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. PolyOne makes no warranties or guarantees respecting suitability of either PolyOne's products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. POLYONE MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.