



Bergamid™ B700 G30 H BLACK

Polyamide 6

Key Characteristics

Product Description	
Glass fiber reinforced PA6 compound with heat stabilized.	
General	
Material Status	• Commercial: Active
Regional Availability	• Asia Pacific
Filler / Reinforcement	• Glass Fiber, 30% Filler by Weight
Features	• Heat Stabilized
Appearance	• Black
Processing Method	• Injection Molding

Technical Properties ¹

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density / Specific Gravity	1.36	1.36	ISO 1183
Molding Shrinkage	0.30 to 0.60 %	0.30 to 0.60 %	ASTM D955
Mechanical	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Strength	24700 psi	170 MPa	ISO 527-2
Flexural Modulus	1.16E+6 psi	8000 MPa	ISO 178
Flexural Strength	34100 psi	235 MPa	ISO 178
Impact	Typical Value (English)	Typical Value (SI)	Test Method
Charpy Notched Impact Strength (73°F (23°C))	4.3 ft·lb/in ²	9.0 kJ/m ²	ISO 179
Thermal	Typical Value (English)	Typical Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
264 psi (1.8 MPa), Unannealed, 0.126 in (3.20 mm)	410 °F	210 °C	
Electrical	Typical Value (English)	Typical Value (SI)	Test Method
Surface Resistivity	> 1.0E+12 ohms	> 1.0E+12 ohms	ASTM D257
Flammability	Typical Value (English)	Typical Value (SI)	Test Method
Flame Rating			UL 94
0.028 in (0.70 mm)	HB	HB	
0.06 in (1.5 mm)	HB	HB	
0.12 in (3.0 mm)	HB	HB	

Processing Information

Injection	Typical Value (English)	Typical Value (SI)
Drying Temperature	176 to 212 °F	80 to 100 °C
Drying Time	4.0 to 6.0 hr	4.0 to 6.0 hr
Rear Temperature	428 to 518 °F	220 to 270 °C
Middle Temperature	428 to 518 °F	220 to 270 °C
Front Temperature	428 to 518 °F	220 to 270 °C
Mold Temperature	140 to 176 °F	60 to 80 °C

Copyright © 2019 PolyOne Corporation. PolyOne makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. PolyOne makes no warranties or guarantees respecting suitability of either PolyOne's products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. POLYONE MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.

Injection Notes

Injection Pressure: MED-HIGH
Hold Pressure: MED-HIGH
Screw Speed: MODERATE
Back Pressure: LOW

Notes

¹ Typical values are not to be construed as specifications.

CONTACT INFORMATION**Americas**

United States - Avon Lake
+1 440 930 1000

United States - McHenry
+1 815 385 8500

Asia

China - Guangzhou
+86 20 8732 7260

China - Shenzhen
+86 755 2969 2888

China - Suzhou
+86 512 6823 24 38

China - Suzhou
+86 512 6265 2600

Hong Kong -
+852 2690 5332

Taiwan - Yonghe City,
+886 9396 99740, +886 2929 1849

Europe

Germany - Gaggenau
+49 7225 6802 0

Spain - Barbastro (Huesca)
+34 974 310 314



Beyond Polymers.

Better Business Solutions.™

www.polyone.com

PolyOne Americas

33587 Walker Road
Avon Lake, Ohio 44012
United States
+1 440 930 1000
+1 866 POLYONE

PolyOne Asia

No. 88 Guoshoujing Road
Z.J Hi-tech Park, Pudong
Shanghai, 201203, China
+86 21 5080 1188

PolyOne Europe

6 Giällewee
+352 269 050 35

Copyright ©, 2019 PolyOne Corporation. PolyOne makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. PolyOne makes no warranties or guarantees respecting suitability of either PolyOne's products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. POLYONE MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.