



LubriOne™ NY-30GF/15T NATURAL

Polyamide 6

Key Characteristics

Product Description

LubriOne™ Lubricated and Wear-Resistant Compounds have been specifically formulated to be self-lubricating materials, offering low coefficient of friction and improved wear resistance properties. LubriOne compounds have been demonstrated to reduce friction, noise, vibration, heat buildup and improve product durability.

General

Material Status	• Commercial: Active		
Regional Availability	• Africa & Middle East	• Europe	
Features	• Filled • Low Friction	• Lubricated • Wear Resistant	
Uses	• Appliance Components • Automotive Applications • Bearings • Business Equipment	• Consumer Applications • Conveyor Parts • Gears • Industrial Applications	• Printer Parts • Pulleys • Rollers
Appearance	• Natural Color		
Forms	• Pellets		
Processing Method	• Injection Molding		

Technical Properties ¹

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density ²	1.47 g/cm ³	1.47 g/cm ³	ISO 1183
Mechanical	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Modulus	1.20E+6 psi	8300 MPa	ISO 527-2
Tensile Stress	20300 psi	140 MPa	ISO 527-2
Tensile Strain (Break)	< 3.3 %	< 3.3 %	ISO 527-2
Flexural Modulus	1.09E+6 psi	7500 MPa	ISO 178
Impact	Typical Value (English)	Typical Value (SI)	Test Method
Charpy Notched Impact Strength (73°F (23°C))	4.8 ft-lb/in ²	10 kJ/m ²	ISO 179
Charpy Unnotched Impact Strength 73°F (23°C)	38 ft-lb/in ²	80 kJ/m ²	ISO 179
Thermal	Typical Value (English)	Typical Value (SI)	Test Method
Heat Deflection Temperature 66 psi (0.45 MPa), Unannealed	428 °F	220 °C	ISO 75-2/B
Heat Deflection Temperature 264 psi (1.8 MPa), Unannealed	410 °F	210 °C	ISO 75-2/A
Melting Temperature (DSC)	419 to 437 °F	215 to 225 °C	ISO 3146
Flammability	Typical Value (English)	Typical Value (SI)	Test Method
Flame Rating			UL 94
0.031 in (0.8 mm)	HB	HB	
0.06 in (1.6 mm)	HB	HB	

Processing Information

Injection	Typical Value (English)	Typical Value (SI)
Drying Temperature	176 °F	80 °C
Drying Time	3.0 hr	3.0 hr

Copyright © 2019 PolyOne Corporation. PolyOne makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. PolyOne makes no warranties or guarantees respecting suitability of either PolyOne's products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. POLYONE MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.

Injection	Typical Value (English)	Typical Value (SI)
Processing (Melt) Temp	500 to 554 °F	260 to 290 °C
Mold Temperature	122 to 194 °F	50 to 90 °C

Notes

¹ Typical values are not to be construed as specifications.

² +/-0.02

CONTACT INFORMATION**Americas**

United States - Avon Lake
+1 440 930 1000

United States - McHenry
+1 815 385 8500

Asia

China - Guangzhou
+86 20 8732 7260

China - Shenzhen
+86 755 2969 2888

China - Suzhou
+86 512 6823 24 38

China - Suzhou
+86 512 6265 2600

Hong Kong -
+852 2690 5332

Taiwan - Yonghe City,
+886 9396 99740, +886 2929 1849

Europe

Germany - Gaggenau
+49 7225 6802 0

Spain - Barbastro (Huesca)
+34 974 310 314



Beyond Polymers.

Better Business Solutions. SM

www.polyone.com

PolyOne Americas

33587 Walker Road
Avon Lake, Ohio 44012
United States
+1 440 930 1000
+1 866 POLYONE

PolyOne Asia

No. 88 Guoshoujing Road
Z.J Hi-tech Park, Pudong
Shanghai, 201203, China
+86 21 5080 1188

PolyOne Europe

6 Giällewee
+352 269 050 35

Copyright ©, 2019 PolyOne Corporation. PolyOne makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. PolyOne makes no warranties or guarantees respecting suitability of either PolyOne's products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. POLYONE MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.