



Versollan™ RU 2205-9

Thermoplastic Elastomer

Key Characteristics

Product Description

Versollan™ RU 2205-9 is a high performance, injection moldable TPU alloy developed to offer a rubbery feel and appearance, reduced cycle times, and performance properties associated with TPUs.

- Bonds to PC, ABS, PC/ABS, and Copolyester
- Excellent Abrasion Resistance
- Fast Set Up Rates During Processing
- Matte Finish
- Rubbery, Soft Touch Feel
- Very Good Oil Resistance

General

Material Status	• Commercial: Active		
Regional Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• Abrasion Resistant • Oil Resistant		
Uses	• Consumer Applications • Furniture	• Overmolding • Power/Other Tools	• Soft Touch Applications
RoHS Compliance	• RoHS Compliant		
Appearance	• Black		
Forms	• Pellets		
Processing Method	• Extrusion	• Injection Molding	

Technical Properties ¹

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Specific Gravity	1.16	1.16	ASTM D792
Melt Mass-Flow Rate (MFR)			ASTM D1238
190°C/2.16 kg	7.0 g/10 min	7.0 g/10 min	
200°C/5.0 kg	67 g/10 min	67 g/10 min	
Molding Shrinkage - Flow	0.010 to 0.015 in/in	1.0 to 1.5 %	ASTM D955
Elastomers	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Stress ^{2,3} (100% Strain, 73°F (23°C))	380 psi	2.62 MPa	ASTM D412
Tensile Stress ^{2,3} (300% Strain, 73°F (23°C))	610 psi	4.21 MPa	ASTM D412
Tensile Strength ^{2,3} (Break, 73°F (23°C))	2000 psi	13.8 MPa	ASTM D412
Tensile Elongation ^{2,3} (Break, 73°F (23°C))	710 %	710 %	ASTM D412
Tear Strength	270 lbf/in	47.3 kN/m	ASTM D624
Compression Set (73°F (23°C), 22 hr)	34 %	34 %	ASTM D395B
Hardness	Typical Value (English)	Typical Value (SI)	Test Method
Durometer Hardness (Shore A, 10 sec)	65	65	ASTM D2240
Thermal	Typical Value (English)	Typical Value (SI)	Test Method
Brittleness Temperature ⁴	-88.6 °F	-67.0 °C	ASTM D746
Fill Analysis	Typical Value (English)	Typical Value (SI)	Test Method
Apparent Viscosity			ASTM D3835
392°F (200°C), 11200 sec ⁻¹	14.1 Pa·s	14.1 Pa·s	

Copyright © 2016 PolyOne Corporation. PolyOne makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. PolyOne makes no warranties or guarantees respecting suitability of either PolyOne's products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. POLYONE MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.

Processing Information

Injection	Typical Value (English)	Typical Value (SI)
Drying Temperature	125 to 130 °F	51.7 to 54.4 °C
Drying Time	3.0 to 4.0 hr	3.0 to 4.0 hr
Suggested Max Moisture	< 0.030 %	< 0.030 %
Suggested Max Regrind	20 %	20 %
Rear Temperature	335 to 370 °F	168 to 188 °C
Middle Temperature	355 to 390 °F	179 to 199 °C
Front Temperature	375 to 410 °F	191 to 210 °C
Nozzle Temperature	375 to 420 °F	191 to 216 °C
Processing (Melt) Temp	370 to 410 °F	188 to 210 °C
Mold Temperature	70.0 to 90.0 °F	21.1 to 32.2 °C
Back Pressure	0.00 to 125 psi	0.00 to 0.862 MPa
Screw Speed	75 to 125 rpm	75 to 125 rpm

Injection Notes

Purge thoroughly before and after use of this product with a low flow (0.5 - 2.5 MFR) polyethylene (PE) or polypropylene (PP).

Regrind levels up to 20% can be used with Versollan™ RU 2205-9 with minimal property loss, provided that the regrind is free of contamination. To minimize losses during molding, the melt temperature should remain as low as possible. The final determination of regrind effectiveness should be determined by the customer.

Versollan™ RU 2205-9 should not be left in the barrel for extended idle periods (greater than 5 minutes).

Suggested Dewpoint: -40°F

Injection Speed: 0.5 to 2 in/sec

1st Stage - Boost Pressure: 300 to 700 psi

2nd Stage - Hold Pressure: 30% of Boost

Hold Time (Thick Part): 4 to 10 sec

Hold Time (Thin Part): 1 to 3 sec

Notes

¹ Typical values are not to be construed as specifications.

² Die C

³ 2 hr

⁴ Thickness = 1.91mm

Conditioned for 40hrs at 23C at 50% RH

CONTACT INFORMATION**Americas**

United States - Avon Lake
+1 440 930 1000

United States - McHenry
+1 815 385 8500

Asia

China - Guangzhou
+86 20 8732 7260

China - Shenzhen
+86 755 2969 2888

China - Suzhou
+86 512 6823 24 38

China - Suzhou
+86 512 6265 2600

Hong Kong -
+852 2690 5332

Taiwan - Yonghe City,
+886 9396 99740, +886 2929 1849

Europe

Germany - Gaggenau
+49 7225 6802 0

Spain - Barbastro (Huesca)
+34 974 310 314



Beyond Polymers.

Better Business Solutions.™

www.polyone.com

PolyOne Americas

33587 Walker Road
Avon Lake, Ohio 44012
United States
+1 440 930 1000
+1 866 POLYONE

PolyOne Asia

No. 88 Guoshoujing Road
Z.J Hi-tech Park, Pudong
Shanghai, 201203, China
+86 21 5080 1188

PolyOne Europe

6 Giällewee
+352 269 050 35

Copyright ©, 2016 PolyOne Corporation. PolyOne makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. PolyOne makes no warranties or guarantees respecting suitability of either PolyOne's products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. POLYONE MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.