



## Syncure™ S1060A Natural Crosslinked Polyethylene

### Key Characteristics

#### Product Description

Graft Resin component for PolyOne's Syncure™ system, which is a two-step, silane-grafted, moisture-crosslinkable polyethylene system. Graft Resins have approximate shelf life of 6 months from the date of production. Please consult PolyOne for its use past 6 months.

#### General

Material Status	• Commercial: Active
Regional Availability	• Africa & Middle East • Asia Pacific • Europe • North America
Uses	• Wire & Cable Applications
Forms	• Pellets

### Technical Properties <sup>1</sup>

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density	0.924 g/cm <sup>3</sup>	0.924 g/cm <sup>3</sup>	ASTM D1505
Apparent Density <sup>2</sup>	0.50 g/cm <sup>3</sup>	0.50 g/cm <sup>3</sup>	Internal Method
Melt Mass-Flow Rate (MFR) <sup>3</sup> (190°C/2.16 kg)	0.73 g/10 min	0.73 g/10 min	ASTM D1238
Gel Content <sup>4</sup>	75 %	75 %	ASTM D2765
Mechanical	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Modulus <sup>5</sup>	1600 psi	11.0 MPa	ASTM D638
Tensile Strength <sup>5</sup> (Break)	2400 psi	16.5 MPa	ASTM D638
Tensile Elongation <sup>5</sup> (Break)	600 %	600 %	ASTM D638
Thermal	Typical Value (English)	Typical Value (SI)	Test Method
Deformation <sup>6</sup> (268°F (131°C))	5.7 %	5.7 %	UL 1581
Hot Creep Elongation <sup>7</sup>	45 %	45 %	

#### Additional Information

Tensile, Elongation, Deformation, Hot Creep, and Gel measured on a 95 phr S1060A / 5 phr S1000B system; and cured by autoclave for 9 hours.

### Processing Information

Injection	Typical Value (English)	Typical Value (SI)
Drying Temperature	160 °F	71.1 °C
Drying Time	3.0 to 4.0 hr	3.0 to 4.0 hr
Rear Temperature	400 to 420 °F	204 to 216 °C
Middle Temperature	340 to 400 °F	171 to 204 °C
Front Temperature	350 to 400 °F	177 to 204 °C
Nozzle Temperature	350 to 420 °F	177 to 216 °C
Mold Temperature	80.0 to 150 °F	26.7 to 65.6 °C

Copyright © 2016 PolyOne Corporation. PolyOne makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. PolyOne makes no warranties or guarantees respecting suitability of either PolyOne's products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. POLYONE MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.

**Notes**<sup>1</sup> Typical values are not to be construed as specifications.<sup>2</sup> Geon® 1169<sup>3</sup> Procedure A<sup>4</sup> Crosslinked PE, Method B (NonReferee Test)<sup>5</sup> Type IV, 20 in/min (510 mm/min)<sup>6</sup> 500 g, 1hr<sup>7</sup> SYV-40**CONTACT INFORMATION****Americas**United States - Avon Lake  
+1 440 930 1000United States - McHenry  
+1 815 385 8500**Asia**China - Guangzhou  
+86 20 8732 7260China - Shenzhen  
+86 755 2969 2888China - Suzhou  
+86 512 6823 24 38China - Suzhou  
+86 512 6265 2600Hong Kong -  
+852 2690 5332Taiwan - Yonghe City,  
+886 9396 99740, +886 2929 1849**Europe**Germany - Gaggenau  
+49 7225 6802 0Spain - Barbastró (Huesca)  
+34 974 310 314*Beyond Polymers.**Better Business Solutions.™*

www.polyone.com

**PolyOne Americas**33587 Walker Road  
Avon Lake, Ohio 44012  
United States  
+1 440 930 1000  
+1 866 POLYONE**PolyOne Asia**No. 88 Guoshoujing Road  
Z.J Hi-tech Park, Pudong  
Shanghai, 201203, China  
+86 21 5080 1188**PolyOne Europe**6 Giallewee  
+352 269 050 35

Copyright ©, 2016 PolyOne Corporation. PolyOne makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. PolyOne makes no warranties or guarantees respecting suitability of either PolyOne's products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. POLYONE MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.