



Syncure™ System S110FV-UV

Crosslinked Polyethylene

Key Characteristics

Product Description	
Syncure™ systems are two part moisture crosslinkable insulation compounds. S110FV-UV is a UL bulletinized, RoHS compliant, high strength, highly flame retardant insulation compound. Available in black and natural colorable versions. S110FV-UV is suitable for UL4703 photovoltaic wire insulation not requiring an outer jacket. Graft resin component of this system has approximate shelf life of 6 months from the date of production. Please consult PolyOne for its use past 6 months.	
General	
Material Status	• Commercial: Active
Regional Availability	• North America
Features	• Flame Retardant • Oil Resistant • Low Temperature Resistant • Sunlight Resistant (720 hours)
Uses	• Insulation • Solar Panels • Wire & Cable Applications
Wire Types	• SIS • XHHW • XHH • XHHW-2
Agency Ratings	• UL 44 • UL VW-1 • UL 4703 • USE 2
Appearance	• Black • Natural Color
Forms	• Pellets
Processing Method	• Extrusion Coating

Technical Properties 1

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Specific Gravity	1.29	1.29 g/cm ³	ASTM D792
Gel Content 2	60 %	60 %	ASTM D2765
Mechanical	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Strength 3 (Yield)	2500 psi	17.2 MPa	ASTM D638
Tensile Elongation 3 (Break)	400 %	400 %	ASTM D638
Hardness	Typical Value (English)	Typical Value (SI)	Test Method
Durometer Hardness			ASTM D2240
Shore D	54	54	
Shore D, 10 sec	50	50	
Thermal	Typical Value (English)	Typical Value (SI)	Test Method
UL Temperature Rating	194 °F	90 °C	
Deformation 4 (268°F (131°C))	3.0 %	3.0 %	UL 1581
Aging	Typical Value (English)	Typical Value (SI)	
Retention of Tensile Elongation 5			
250°F (121°C), 75.0 mil (1.91 mm)	94 %	94 %	
Retention of Tensile Strength 5			
250°F (121°C), 75.0 mil (1.91 mm)	100 %	100 %	
Electrical	Typical Value (English)	Typical Value (SI)	Test Method
Dielectric Strength	1000 V/mil	39 kV/mm	ASTM D149
Dielectric Constant (1 MHz)	2.54	2.54	ASTM D150
Dissipation Factor (1 MHz)	2.8E-3	2.8E-3	ASTM D150
Flammability	Typical Value (English)	Typical Value (SI)	Test Method
Oxygen Index (0.0750 in (1.91 mm))	27 %	27 %	ASTM D2863

Copyright ©, 2014 PolyOne Corporation. PolyOne makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. PolyOne makes no warranties or guarantees respecting suitability of either PolyOne's products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. POLYONE MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.

Flammability	Typical Value (English)	Typical Value (SI)	Test Method
Flame Test ⁶	Pass	Pass	UL 1581
Additional Information	Typical Value (English)	Typical Value (SI)	
Catalyst Masterbatch - V-0044G-UV Natural or Black	50 %	50 %	
Grafted Base Resin - S-1060A	50 %	50 %	

NOTE: The above represents Typical Properties measured on 14 AWG with 30 mil wall.

STORAGE AND HANDLING: Use S-1060A within 48 hours once package is open to avoid self-curing and scrap.

Notes

¹ Typical values are not to be construed as specifications.

² Crosslinked PE, Method B (NonReferee Test)

³ Type IV, 20 in/min (510 mm/min)

⁴ 500 g, 1hr

⁵ 336 hr, UL Standard

⁶ Vertical

Copyright ©, 2014 PolyOne Corporation. PolyOne makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. PolyOne makes no warranties or guarantees respecting suitability of either PolyOne's products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. POLYONE MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.