



Maxxam™ SY 89-22-7

Polypropylene

Key Characteristics

Product Description

Maxxam™ SY 89-22-7 is a polypropylene copolymer compound with a pre-dispersed blowing agent for up to 60% expansion. The compound offers consistent cell structure, dielectric properties, and strength on insulation walls as thin as 10 mils.

General

Material Status	• Commercial: Active		
Regional Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• Foamable		
Uses	• Cable Jacketing	• Communication Wire Insulation	• Wire & Cable Applications
RoHS Compliance	• RoHS Compliant		
Forms	• Pellets		
Processing Method	• Extrusion	• Injection Molding	

Technical Properties ¹

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Specific Gravity	0.520	0.520	ASTM D792
Melt Mass-Flow Rate (MFR) ² (190°C/2.16 kg)	2.1 g/10 min	2.1 g/10 min	ASTM D1238
Mechanical	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Strength ³ (Yield)	3400 psi	23.4 MPa	ASTM D638
Tensile Elongation ³ (Break)	400 %	400 %	ASTM D638
Electrical	Typical Value (English)	Typical Value (SI)	Test Method
Dielectric Constant (1 kHz)	2.24	2.24	ASTM D150
Dissipation Factor (1 kHz)	3.0E-4	3.0E-4	ASTM D150

Additional Information

NOTE: 1. Typical properties of molded slab (0.075"); Not to be construed as specifications. 2. Foam density reduction depends upon loading level, temperature and residence time before cooling. 3. Recommended process temperature: 190°C to 220°C (375°F to 430°F).

Notes

¹ Typical values are not to be construed as specifications.

² Procedure A

³ Type IV, 20 in/min (510 mm/min)

CONTACT INFORMATION**Americas**

United States - Avon Lake
+1 440 930 1000

United States - McHenry
+1 815 385 8500

Asia

China - Guangzhou
+86 20 8732 7260

China - Shenzhen
+86 755 2969 2888

China - Suzhou
+86 512 6823 24 38

China - Suzhou
+86 512 6265 2600

Hong Kong -
+852 2690 5332

Taiwan - Yonghe City,
+886 9396 99740, +886 2929 1849

Europe

Germany - Gaggenau
+49 7225 6802 0

Spain - Barbastro (Huesca)
+34 974 310 314



Beyond Polymers.

Better Business Solutions. SM

www.polyone.com

PolyOne Americas

33587 Walker Road
Avon Lake, Ohio 44012
United States
+1 440 930 1000
+1 866 POLYONE

PolyOne Asia

No. 88 Guoshoujing Road
Z.J Hi-tech Park, Pudong
Shanghai, 201203, China
+86 21 5080 1188

PolyOne Europe

6 Giällewee
+352 269 050 35

Copyright ©, 2015 PolyOne Corporation. PolyOne makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. PolyOne makes no warranties or guarantees respecting suitability of either PolyOne's products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. POLYONE MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.