



Stat-Tech™ NY-090911

Polyamide 6

Key Characteristics

Product Description

Stat-Tech™ Electrically Conductive Compounds are specifically engineered to provide anti-static, ESD and RFI/EMI shielding performance for critical electronic equipment applications. These compounds combine the performance of select engineering resins with reinforcing additives such as carbon powder, carbon fiber, nickel-coated carbon fiber and stainless steel fiber for low to high levels of conductivity depending upon application requirements.

General

Material Status	• Commercial: Active
Regional Availability	• Europe
Features	• Conductive
Forms	• Pellets
Processing Method	• Injection Molding

Technical Properties ¹

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density	1.13 to 1.17 g/cm ³	1.13 to 1.17 g/cm ³	ISO 1183
Mechanical	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Modulus	363000 psi	2500 MPa	ISO 527-2
Tensile Stress	5800 psi	40.0 MPa	ISO 527-2
Tensile Strain (Break)	2.0 %	2.0 %	ISO 527-2
Flexural Modulus	392000 psi	2700 MPa	ISO 178
Flexural Stress	10200 psi	70.0 MPa	ISO 178
Impact	Typical Value (English)	Typical Value (SI)	Test Method
Charpy Notched Impact Strength (73°F (23°C))	2.4 ft·lb/in ²	5.0 kJ/m ²	ISO 179
Charpy Unnotched Impact Strength 73°F (23°C)	19 ft·lb/in ²	40 kJ/m ²	ISO 179
Thermal	Typical Value (English)	Typical Value (SI)	Test Method
Melting Temperature (DSC)	419 to 437 °F	215 to 225 °C	ISO 3146
Electrical	Typical Value (English)	Typical Value (SI)	Test Method
Surface Resistivity	< 1.0E+5 ohms	< 1.0E+5 ohms	IEC 60093
Comparative Tracking Index (CTI)	600 V	600 V	UL 746
Flammability	Typical Value (English)	Typical Value (SI)	Test Method
Flame Rating (0.13 in (3.2 mm))	HB	HB	UL 94

Processing Information

Injection	Typical Value (English)	Typical Value (SI)
Drying Temperature	176 to 212 °F	80 to 100 °C
Drying Time	4.0 hr	4.0 hr
Processing (Melt) Temp	482 to 518 °F	250 to 270 °C
Mold Temperature	140 to 176 °F	60 to 80 °C

Notes

¹ Typical values are not to be construed as specifications.