



Stat-Tech™ PC-10CF/000 FC BLACK

Polycarbonate

Key Characteristics

Product Description	
Carbon Fiber Reinforced Polycarbonate Compound	
General	
Material Status	• Commercial: Active
Regional Availability	• Asia Pacific
Filler / Reinforcement	• Carbon Fiber
Appearance	• Black
Processing Method	• Injection Molding

Technical Properties ¹

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density / Specific Gravity	1.24	1.24	ASTM D792
Molding Shrinkage (0.118 in (3.00 mm))	0.20 to 0.40 %	0.20 to 0.40 %	Internal Method
Mechanical	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Strength ²	14500 psi	100 MPa	ASTM D638
Tensile Elongation ² (Break)	2.5 %	2.5 %	ASTM D638
Flexural Modulus ³	943000 psi	6500 MPa	ASTM D790
Flexural Strength ³	21800 psi	150 MPa	ASTM D790
Impact	Typical Value (English)	Typical Value (SI)	Test Method
Notched Izod Impact 73°F (23°C), 0.126 in (3.20 mm), Injection Molded	1.3 ft-lb/in	70 J/m	ASTM D256A
Thermal	Typical Value (English)	Typical Value (SI)	Test Method
Deflection Temperature Under Load 264 psi (1.8 MPa), Unannealed	284 °F	140 °C	ASTM D648
Electrical	Typical Value (English)	Typical Value (SI)	Test Method
Surface Resistivity	1.0E+2 to 5.0E+4 ohms	1.0E+2 to 5.0E+4 ohms	ASTM D257
Flammability	Typical Value (English)	Typical Value (SI)	Test Method
Flame Rating (0.12 in (3.0 mm))	V-0	V-0	Internal Method

Processing Information

Injection	Typical Value (English)	Typical Value (SI)
Drying Temperature	230 to 266 °F	110 to 130 °C
Drying Time	4.0 to 6.0 hr	4.0 to 6.0 hr
Processing (Melt) Temp	536 to 590 °F	280 to 310 °C
Mold Temperature	176 to 248 °F	80 to 120 °C

Injection Notes
Injection Pressure: MED-HIGH
Hold Pressure: MED-HIGH
Screw Speed: MODERATE
Back Pressure: LOW

Notes

¹ Typical values are not to be construed as specifications.

² 0.20 in/min (5.0 mm/min)

³ 0.051 in/min (1.3 mm/min)



Beyond Polymers.

Better Business Solutions. SM