



# Stat-Tech™ PP-16CP/000-2HI BLK

## Polypropylene

### Key Characteristics

Product Description	
Carbon powder filled electrically conductive PP compound	
General	
Material Status	• Commercial: Active
Regional Availability	• Asia Pacific
Filler / Reinforcement	• Carbon Powder, 16% Filler by Weight
Features	• Antistatic • Electrically Conductive
RoHS Compliance	• RoHS Compliant
Forms	• Pellets
Processing Method	• Injection Molding

### Technical Properties <sup>1</sup>

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density / Specific Gravity	1.03	1.03	ASTM D792
Molding Shrinkage - Flow	8.0E-3 to 0.010 in/in	0.80 to 1.0 %	ASTM D955
Mechanical	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Strength (Yield)	3630 psi	25.0 MPa	ASTM D638
Flexural Modulus	232000 psi	1600 MPa	ASTM D790
Flexural Strength	5800 psi	40.0 MPa	ASTM D790
Impact	Typical Value (English)	Typical Value (SI)	Test Method
Notched Izod Impact 73°F (23°C), 0.252 in (6.40 mm), Injection Molded	9.4 ft·lb/in	500 J/m	ASTM D256
Thermal	Typical Value (English)	Typical Value (SI)	Test Method
Deflection Temperature Under Load 66 psi (0.45 MPa), Annealed, 0.125 in (3.18 mm)	203 °F	95.0 °C	ASTM D648
Deflection Temperature Under Load 264 psi (1.8 MPa), Annealed, 0.125 in (3.18 mm)	122 °F	50.0 °C	ASTM D648
Electrical	Typical Value (English)	Typical Value (SI)	Test Method
Surface Resistivity	1000 to 100000 ohms/sq	1000 to 100000 ohms/sq	ASTM D257
Flammability	Typical Value (English)	Typical Value (SI)	Test Method
Flame Rating			UL 94
0.06 in (1.5 mm)	HB	HB	
0.12 in (3.0 mm)	HB	HB	

### Processing Information

Injection	Typical Value (English)	Typical Value (SI)
Processing (Melt) Temp	392 to 428 °F	200 to 220 °C

#### Notes

<sup>1</sup> Typical values are not to be construed as specifications.