



Stat-Tech™ ST7300-8045 EI OOV GREY6

Acrylonitrile Butadiene Styrene

Key Characteristics

Product Description	
Permanent antistatic and high heat resistant ABS compound	
General	
Material Status	• Commercial: Active
Regional Availability	• Asia Pacific
Filler / Reinforcement	• Glass Fiber, 5.0% Filler by Weight
Features	• Antistatic • High Heat Resistance
Appearance	• Dark Grey
Forms	• Pellets
Processing Method	• Injection Molding

Technical Properties ¹

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density / Specific Gravity	1.09	1.09	ASTM D792
Molding Shrinkage	0.40 to 0.70 %	0.40 to 0.70 %	ASTM D955
Mechanical	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Strength ²	5800 psi	40.0 MPa	ASTM D638
Flexural Modulus ³	305000 psi	2100 MPa	ASTM D790
Flexural Strength ³	8700 psi	60.0 MPa	ASTM D790
Impact	Typical Value (English)	Typical Value (SI)	Test Method
Notched Izod Impact (Injection Molded)	5.6 ft-lb/in	300 J/m	ASTM D256A
Thermal	Typical Value (English)	Typical Value (SI)	Test Method
Deflection Temperature Under Load 264 psi (1.8 MPa), Unannealed	140 °F	60.0 °C	ASTM D648
Electrical	Typical Value (English)	Typical Value (SI)	Test Method
Surface Resistivity	1.0E+10 to 1.0E+11 ohms	1.0E+10 to 1.0E+11 ohms	ASTM D257
Flammability	Typical Value (English)	Typical Value (SI)	Test Method
Flame Rating			UL 94
0.030 in (0.75 mm)	HB	HB	
0.06 to 0.12 in (1.5 to 3.0 mm)	HB	HB	

Processing Information

Injection	Typical Value (English)	Typical Value (SI)
Drying Temperature	176 to 185 °F	80 to 85 °C
Drying Time	2.0 to 3.0 hr	2.0 to 3.0 hr
Processing (Melt) Temp	392 to 464 °F	200 to 240 °C
Mold Temperature	149 to 185 °F	65 to 85 °C

Injection Notes	
Injection Pressure: MED-HIGH	
Hold Pressure: MED-HIGH	
Screw Speed: MODERATE	
Back Pressure: LOW	

Notes

¹ Typical values are not to be construed as specifications.

² 0.20 in/min (5.0 mm/min)

³ 0.051 in/min (1.3 mm/min)