



# Versaflex™ G 7400-60 N

## Thermoplastic Elastomer

### Key Characteristics

#### Product Description

Versaflex™ G 7400-60 N is an easy processing, general purpose TPE designed for a wide variety of applications, and may be appropriate where FDA and EU 10/2011 compliances are required.

- Non-Slip Grip
- Overmold Adhesion to Polypropylene
- Soft Touch, Rubbery Feel

#### General

Material Status	• Commercial: Active
Regional Availability	• Europe
Features	<ul style="list-style-type: none"> <li>• General Purpose</li> <li>• Good Colorability</li> </ul>
Uses	<ul style="list-style-type: none"> <li>• Consumer Applications</li> <li>• Flexible Grips</li> <li>• Gaskets</li> </ul>
Agency Ratings	<ul style="list-style-type: none"> <li>• EU 10/2011 <sup>1</sup></li> <li>• FDA 21 CFR 177.1210 <sup>1</sup></li> </ul>
RoHS Compliance	• RoHS Compliant
Appearance	• Natural Color
Forms	• Pellets
Processing Method	• Injection Molding

### Technical Properties <sup>2</sup>

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density (73°F (23°C), Natural)	1.20 g/cm <sup>3</sup>	1.20 g/cm <sup>3</sup>	ISO 1183
Melt Volume-Flow Rate (MVR) (190°C/5.0 kg)	200 cm <sup>3</sup> /10min	200 cm <sup>3</sup> /10min	ISO 1133
Molding Shrinkage - Flow (0.0787 in (2.00 mm))	1.3 to 2.1 %	1.3 to 2.1 %	ISO 294-4
Elastomers	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Stress <sup>3</sup>			DIN 53504-S2
100% Strain, 73°F (23°C), 0.0787 in (2.00 mm)	268 psi	1.85 MPa	
Tensile Stress <sup>3</sup>			DIN 53504-S2
300% Strain, 73°F (23°C), 0.0787 in (2.00 mm)	348 psi	2.40 MPa	
Tensile Strength <sup>3</sup>			DIN 53504-S2
Break, 73°F (23°C), 0.0787 in (2.00 mm)	870 psi	6.00 MPa	
Tensile Elongation <sup>3</sup>			DIN 53504-S2
Break, 73°F (23°C), 0.0787 in (2.00 mm)	800 %	800 %	
Tear Strength			ISO 34-1
73°F (23°C), 0.0787 in (2.00 mm)	134 lbf/in	23.5 kN/m	
Compression Set			ISO 815
73°F (23°C), 72 hr	25 %	25 %	
158°F (70°C), 22 hr	53 %	53 %	
212°F (100°C), 22 hr	76 %	76 %	

Hardness	Typical Value (English)	Typical Value (SI)	Test Method
Durometer Hardness <sup>4</sup>			ISO 7619
Shore A, 10 sec, 73°F (23°C), Injection Molded	60	60	
Flammability	Typical Value (English)	Typical Value (SI)	Test Method
Flame Rating (0.06 in (1.5 mm))	HB	HB	UL 94
Fill Analysis	Typical Value (English)	Typical Value (SI)	Test Method
Apparent Viscosity			ASTM D3835
392°F (200°C), 11200 sec <sup>-1</sup>	7.80 Pa·s	7.80 Pa·s	

### Processing Information

Injection	Typical Value (English)	Typical Value (SI)
Suggested Max Regrind	20 %	20 %
Rear Temperature	320 to 370 °F	160 to 188 °C
Middle Temperature	350 to 380 °F	177 to 193 °C
Front Temperature	370 to 410 °F	188 to 210 °C
Nozzle Temperature	370 to 420 °F	188 to 216 °C
Mold Temperature	60 to 100 °F	16 to 38 °C
Back Pressure	0.00 to 120 psi	0.00 to 0.827 MPa
Screw Speed	40 to 100 rpm	40 to 100 rpm

### Notes

<sup>1</sup> Product rating may be influenced by end product design and/or conditions of use. Please contact GLS Thermoplastic Elastomers for information addressing EU (EU, 10/2011) and FDA (21 CFR 177.1210) compliance.

<sup>2</sup> Typical values are not to be construed as specifications.

<sup>3</sup> 7.9 in/min (200 mm/min)

<sup>4</sup> ± 5 Sh A



*Beyond Polymers.*

*Better Business Solutions.™*