

Technical Data Sheet



**CELLIDOR CP 300.02-16**

|                        |   |
|------------------------|---|
| Base Polymer           | CelluloseAcetatePropionate                  |
| Filler/Additive System | phthalate-free plasticiser,light stabiliser |
| Market Segment         | Medical / Personal Care                     |
| Typical Applications   | various                                     |

|                               |  |
|-------------------------------|--|
| Pre-Drying Conditions         | in an air circulating dryer 50-80 °C<br>for 2-4 h<br>dependant on moisture content |
| Processing Injection Moulding | melt temperature 180-230 °C<br>mould temperature 40-80 °C                          |
| Storage                       | dry, protected from light  |

| Properties                              | Value     | Dimension              | Test Norm   |
|---|-----------|------------------------|-------------|
| <b>Mechanical Properties</b>            |           |                        |             |
| Flexural Modulus                        | 1350      | MPa                    | ISO 178     |
| Flexural Stress (3.5% Strain)           | 35        | MPa                    | ISO 178     |
| Tensile Modulus                         | 1350      | MPa                    | ISO 527     |
| Tensile Stress at Yield                 | 30        | MPa                    | ISO 527     |
| Tensile Elongation at Yield             | 3.6       | %                      | ISO 527     |
| Tensile Elongation at Break             | 28        | %                      | ISO 527     |
| Impact Strength (Charpy, 23°C)          | no break  | kJ/m <sup>2</sup>      | ISO 179/1eU |
| Impact Strength (Charpy, -40°C)         | 200       | kJ/m <sup>2</sup>      | ISO 179/1eU |
| Notched Impact Strength (Charpy, 23°C)  | 32        | kJ/m <sup>2</sup>      | ISO 179/1eA |
| Notched Impact Strength (Charpy, -40°C) | 7         | kJ/m <sup>2</sup>      | ISO 179/1eA |
| Ball Indentation Hardness H132/30       | 59        | MPa                    | ISO 2039-1  |
| <b>Thermal Properties</b>               |           |                        |             |
| Vicat B50                               | 85        | °C                     | ISO 306     |
| HDT / A (1,8 MPa)                       | 74        | °C                     | ISO 75-1/-2 |
| <b>Rheological Properties</b>           |           |                        |             |
| Melt Index (MVR)                        | 15        | cm <sup>3</sup> /10min | ISO 1133    |
| MVR temperature                         | 210       | °C                     | -           |
| MVR load                                | 2.16      | kg                     | -           |
| Shrinkage (24h)                         | 0.7 - 0.9 | %                      | ISO 294-4   |
| <b>Physical Properties</b>              |           |                        |             |
| Density                                 | 1180      | kg/m <sup>3</sup>      | ISO 1183    |