

Technical Data Sheet



CELLIDOR CP 400-10

Base Polymer	CelluloseAcetatePropionate
Filler/Additive System	10 % phthalate-free plasticiser
Typical Applications	various

Pre-Drying Conditions in an air circulating dryer 60-90 °C
for 2-4 h
dependant on moisture content
0,15 % max. moisture content

Processing Injection Moulding melt temperature 180-230 °C
mould temperature 40-80 °C

Storage dry, protected from light

Properties	Value	Dimension	Test Norm
Mechanical Properties			
Flexural Modulus	1800	MPa	ISO 178
Flexural Stress (3.5% Strain)	50	MPa	ISO 178
Tensile Modulus	1700	MPa	ISO 527
Tensile Stress at Yield	40	MPa	ISO 527
Tensile Elongation at Yield	4.1	%	ISO 527
Tensile Elongation at Break	13	%	ISO 527
Impact Strength (Charpy, 23 °C)	225	kJ/m ²	ISO 179/1eU
Notched Impact Strength (Charpy, 23 °C)	28	kJ/m ²	ISO 179/1eA
Ball Indentation Hardness H358/30	70	MPa	ISO 2039-1
Thermal Properties			
Vicat B50	93	°C	ISO 306
HDT / A (1,8 MPa)	90	°C	ISO 75-1/-2
Rheological Properties			
Melt Index (MVR)	5	cm ³ /10min	ISO 1133
MVR temperature	210	°C	-
MVR load	2.16	kg	-
Shrinkage (24h)	0.4 - 0.7	%	ISO 294-4
Physical Properties			
Density	1210	kg/m ³	ISO 1183