

## Technical Data Sheet



### CELLIDOR CP 430-13 AG

Base Polymer	CelluloseAcetatePropionate
Filler/Additive System	13 % phthalate-free plasticiser
Typical Applications	various

Pre-Drying Conditions in an air circulating dryer 50-80 °C  
for 2-4 h  
dependant on moisture content  
max. moisture content <0,15 %

Processing Injection Moulding melt temperature 180-230 °C  
mould temperature 40-80 °C  
extrusion melt temperature 180-230 °C  
die temperature 40-80 °C

Storage dry, protected from light

Properties	Value	Dimension	Test Norm
<b>Mechanical Properties</b>			
Flexural Modulus	1600	MPa	ISO 178
Flexural Stress (3.5% Strain)	45	MPa	ISO 178
Tensile Modulus	1500	MPa	ISO 527
Tensile Stress at Yield	34	MPa	ISO 527
Tensile Elongation at Yield	3.7	%	ISO 527
Tensile Elongation at Break	19	%	ISO 527
Impact Strength (Charpy, 23°C)	no break	kJ/m <sup>2</sup>	ISO 179/1eU
Impact Strength (Charpy, -40°C)	220	kJ/m <sup>2</sup>	ISO 179/1eU
Notched Impact Strength (Charpy, 23°C)	30	kJ/m <sup>2</sup>	ISO 179/1eA
Notched Impact Strength (Charpy, -40°C)	7	kJ/m <sup>2</sup>	ISO 179/1eA
Ball Indentation Hardness H132/30	75	MPa	ISO 2039-1
<b>Thermal Properties</b>			
Vicat B50	86	°C	ISO 306
HDT / A (1,8 MPa)	82	°C	ISO 75-1/-2
<b>Rheological Properties</b>			
Melt Index (MVR)	9	cm <sup>3</sup> /10min	ISO 1133
MVR temperature	210	°C	-
MVR load	2.16	kg	-
Shrinkage (24h)	0.4 - 0.7	%	ISO 294-4
<b>Physical Properties</b>			
Density	1200	kg/m <sup>3</sup>	ISO 1183