

Technical Data Sheet



ALCOM LD2 HTC 1000 UV CC1044-21

Base Polymer	High Temperature Copolyester
Filler/Additive System	special filler
Special Features	translucent,high light transmission,light scattering,UV stabilised
Market Segment	Automotive,Lighting
Application Area	lighting,light transparent components
Typical Applications	lamp covers,display elements,operating elements

Pre-Drying Conditions	90 °C in a dry air (dessiccant) dryer for 4-6 h max. moisture content <0,03 %
Processing Injection Moulding	melt temperature 260-280 °C mould temperature 50-70 °C
Storage	dry, protected from light

Properties	Value	Dimension	Test Norm
Mechanical Properties			
Flexural Modulus	1700	MPa	ISO 178
Flexural Stress (3.5% Strain)	54	MPa	ISO 178
Tensile Modulus	1700	MPa	ISO 527
Tensile Stress at Yield	47	MPa	ISO 527
Tensile Elongation at Yield	5.8	%	ISO 527
Tensile Elongation at Break	100	%	ISO 527
Impact Strength (Charpy, 23°C)	no break	kJ/m ²	ISO 179/1eU
Impact Strength (Charpy, -40°C)	no break	kJ/m ²	ISO 179/1eU
Notched Impact Strength (Charpy, 23°C)	23	kJ/m ²	ISO 179/1eA
Notched Impact Strength (Charpy, -40°C)	10	kJ/m ²	ISO 179/1eA
Thermal Properties			
Vicat B50	100	°C	ISO 306
HDT / A (1,8 MPa)	86	°C	ISO 75-1/-2
Rheological Properties			
Melt Index (MVR)	20	cm ³ /10min	ISO 1133
MVR temperature	280	°C	-
MVR load	2.16	kg	-
Shrinkage (24h)	0.4 - 0.7	%	ISO 294-4
Physical Properties			
Density	1180	kg/m ³	ISO 1183
Flammability			
Flammability (1.5 mm)	HB	class	UL 94

Technical Data Sheet



ALCOM LD2 HTC 1000 UV CC1044-21

(Last update: 01.02.2024)

Optical Properties

Total Transmission T(Y) (d=1,0mm, A, 2°)	82	%	ISO 13468
Total Transmission T(Y) (d=2,0mm, A, 2°)	69	%	ISO 13468
Total Transmission T(Y) (d=3,0mm, A, 2°)	58	%	ISO 13468
Total Transmission T(Y) (d=4,0mm, A, 2°)	49.5	%	ISO 13468
Haze T(Y) (d=1,0 mm, A, 2°)	94.5	%	ISO 13468
Haze T(Y) (d=2,0 mm, A, 2°)	95.5	%	ISO 13468
Haze T(Y) (d=3,0 mm, A, 2°)	95.5	%	ISO 13468
Haze T(Y) (d=4,0 mm, A, 2°)	95.5	%	ISO 13468