+135-3858-6433 (GuangDong) +188-1699-6168 (ShangHai) +852-6957-5415 (HongKong)

Technical Data Sheet

-- Alcolor®



ALCOLOR PA A GY927-1592

Base Polymer Polyamide 6

Colour grey, similar to RAL 7011

Thermal Stability Colourant 280 °C max.
Light Fastness Colourant blue woolscale 8
For use in Polyamide

Special Features free from cadmium, lead and diarylide pigments, dust-free, high additive

content, high dispersibility

Market Segment various

Application Area injection moulded parts, extruded parts, blow moulded parts

Dosage 3 % injection moulding

dependant on wall thickness and required colour intensity

Pre-Drying Conditions 80 °C in a dry air (dessiccant) dryer

for 2-12 h

dependant on moisture content

Storage dry, protected from light

not above 30°C