

Technical Data Sheet



ALTECH PA6 A 1000/209

Base Polymer	Polyamide 6
Colour	black,blue,grey,natural color,white
Special Features	easy release (demoulding),easy flow,fast solidifying,heat stabilised
Market Segment	electrical and electronic
Application Area	electrical components,injection moulded parts
Typical Applications	thin walled parts,protection caps,functional components

Pre-Drying Conditions	80 °C in a dry air (dessiccant) dryer for 2-12 h dependant on moisture content max. moisture content <0,15 %
-----------------------	---

Processing Injection Moulding	melt temperature 250-270 °C mould temperature 60-100 °C
-------------------------------	--

Storage	dry, protected from light
---------	---------------------------

Properties	dry/cond.	Dimension	Test Norm
Mechanical Properties			
Flexural Modulus	2800 / -	MPa	ISO 178
Flexural Stress (3.5% Strain)	95 / -	MPa	ISO 178
Tensile Modulus	3200 / -	MPa	ISO 527
Tensile Stress at Yield	90 / -	MPa	ISO 527
Tensile Elongation at Yield	3.8 / -	%	ISO 527
Tensile Elongation at Break	15 / -	%	ISO 527
Impact Strength (Charpy, 23°C)	no break / -	kJ/m ²	ISO 179/1eU
Notched Impact Strength (Charpy, 23°C)	4 / -	kJ/m ²	ISO 179/1eA
Thermal Properties			
HDT / A (1,8 MPa)	65 / *	°C	ISO 75-1/-2
DSC (Melt Point)	220 / *	°C	ISO 11357
Rheological Properties			
Shrinkage (lengthwise, 24h)	1.2 - 1.4	%	ISO 294-4
Shrinkage (lateral, 24h)	1.2 - 1.4	%	ISO 294-4
Physical Properties			
Density	1130 / -	kg/m ³	ISO 1183
Flammability			
Flammability (1.5 mm)	V-2 / *	class	UL 94
Yellow Card available	yes / *	-	-