

Technical Data Sheet



ALCOM LD PC 1000 UV 15112 GY1027-16

Base Polymer	Polycarbonate
Filler/Additive System	special filler,UV stabilised
Special Features	translucent,light scattering,high light diffusion,good flow
Market Segment	Automotive,Lighting
Application Area	lighting,light transparent components
Typical Applications	display elements,operating elements
Approvals	GS93016

Pre-Drying Conditions	120 °C in a dry air (dessiccant) dryer for 2-4 h 120 °C in an air circulating dryer for 4-12 h max. moisture content <0,02 %
Processing Injection Moulding	melt temperature 270-310 °C mould temperature 80-110 °C
Storage	dry, protected from light

Properties	Value	Dimension	Test Norm
Mechanical Properties			
Flexural Modulus	2450	MPa	ISO 178
Flexural Stress (3.5% Strain)	76	MPa	ISO 178
Tensile Modulus	2400	MPa	ISO 527
Tensile Stress at Yield	66	MPa	ISO 527
Tensile Elongation at Yield	6	%	ISO 527
Tensile Elongation at Break	70	%	ISO 527
Impact Strength (Charpy, 23°C)	no break	kJ/m ²	ISO 179/1eU
Impact Strength (Charpy, -40°C)	no break	kJ/m ²	ISO 179/1eU
Notched Impact Strength (Charpy, 23°C)	17	kJ/m ²	ISO 179/1eA
Notched Impact Strength (Charpy, -40°C)	13	kJ/m ²	ISO 179/1eA
Thermal Properties			
Vicat B50	142	°C	ISO 306
HDT / A (1,8 MPa)	124	°C	ISO 75-1/-2
Rheological Properties			
Melt Index (MVR)	20	cm ³ /10min	ISO 1133
MVR temperature	300	°C	-
MVR load	1.2	kg	-
Shrinkage (24h)	0.6 - 0.9	%	ISO 294-4
Physical Properties			
Density	1190	kg/m ³	ISO 1183

Technical Data Sheet



ALCOM LD PC 1000 UV 15112 GY1027-16

Flammability

Flammability (0.75 mm)

Yellow Card available

Flammability (1.5 mm)

Yellow Card available

Glow Wire (GWFI, 850 °C, 1.0mm)

Glow Wire (GWFI, 850 °C, 2.0mm)

Fire behavior FMVSS (1.0 mm)

V-2

class

UL 94

yes

-

-

HB

class

UL 94

yes

-

-

passed

-

DIN EN 60695

passed

-

DIN EN 60695

passed

-

FMVSS 302/DIN

75200

Optical Properties

Total Transmission T(Y) (d=1,0mm, A, 2°)

9.5

%

ISO 13468

Haze T(Y) (d=1,0 mm, A, 2°)

95.5

%

ISO 13468

Half Power Angle T(Y) (d=1,0mm, A, 2°)


54

°


-

Diagrams

Stress-Strain



Angle dependent relative irradiance



Technical Data Sheet



ALCOM LD PC 1000 UV 15112 GY1027-16

Spectrum

