

## Technical Data Sheet



### ALCOM LIR PC 1000 UV 14099 BK1203-14

Base Polymer	Polycarbonate
Filler/Additive System	UV stabilised
Special Features	IR-transparent
Market Segment	Automotive, Lighting
Application Area	lighting, IR-transparent
Typical Applications	lamp covers, display elements, operating elements

Pre-Drying Conditions	120 °C in a dry air (dessiccant) dryer for 2-3 h max. moisture content <0,02 %
Processing Injection Moulding	melt temperature 270-310 °C mould temperature 80-110 °C
Storage	dry, protected from light

Properties	Value	Dimension	Test Norm
<b>Mechanical Properties</b>			
Flexural Modulus	2450	MPa	ISO 178
Flexural Stress (3.5% Strain)	76	MPa	ISO 178
Tensile Modulus	2400	MPa	ISO 527
Tensile Stress at Yield	66	MPa	ISO 527
Tensile Elongation at Yield	6	%	ISO 527
Tensile Elongation at Break	90	%	ISO 527
Impact Strength (Charpy, 23°C)	no break	kJ/m <sup>2</sup>	ISO 179/1eU
Impact Strength (Charpy, -40°C)	no break	kJ/m <sup>2</sup>	ISO 179/1eU
Notched Impact Strength (Charpy, 23°C)	10	kJ/m <sup>2</sup>	ISO 179/1eA
Notched Impact Strength (Charpy, -40°C)	10	kJ/m <sup>2</sup>	ISO 179/1eA
<b>Thermal Properties</b>			
Vicat B50	142	°C	ISO 306
HDT / A (1,8 MPa)	124	°C	ISO 75-1/-2
<b>Rheological Properties</b>			
Melt Index (MVR)	16	cm <sup>3</sup> /10min	ISO 1133
MVR temperature	300	°C	-
MVR load	1.2	kg	-
Shrinkage (24h)	0.6 - 0.8	%	ISO 294-4
<b>Physical Properties</b>			
Density	1190	kg/m <sup>3</sup>	ISO 1183
<b>Flammability</b>			
Flammability (0.75 mm)	V-2	class	UL 94

Technical Data Sheet



**ALCOM LIR PC 1000 UV 14099 BK1203-14**


Flammability (1.5 mm)	HB	class	UL 94
Glow Wire (GWFI, 850°C, 1.0mm)	passed	-	DIN EN 60695
Glow Wire (GWFI, 850°C, 2.0mm)	passed	-	DIN EN 60695

**Optical Properties**

Total Transmission T(Y) (d=1,0mm, A, 2°)	0.2	%	ISO 13468
Spectral Transmission 800nm (d=1,0mm)	93	%	ISO 13468

**Diagrams**

**Angle dependent relative irradiance**



**Spectrum**

