

Technical Data Sheet



TEDUR L 9422-1



Base Polymer	Polyphenylene Sulphide
Filler/Additive System	30 % glass fibres, 15 % PTFE
Special Features	improved sliding / wear, high stiffness, high toughness
Market Segment	Automotive, Machinery
Typical Applications	bearings and sliding elements, functional components

Pre-Drying Conditions	in a dry air (dessiccant) dryer 130-140 °C for 2-4 h dependant on moisture content
Processing Injection Moulding	melt temperature 320-340 °C mould temperature >140 °C
Storage	dry, protected from light

Properties	Value	Dimension	Test Norm
Mechanical Properties			
Flexural Modulus	10500	MPa	ISO 178
Flexural Strength	230	MPa	ISO 178
Flexural Deflection (Maximum Force)	2.4	%	ISO 178
Tensile Modulus	12000	MPa	ISO 527
Tensile Strength at Break	155	MPa	ISO 527
Tensile Elongation at Break	2	%	ISO 527
Impact Strength (Charpy, 23°C)	40	kJ/m²	ISO 179/1eU
Thermal Properties			
HDT / A (1,8 MPa)	275	°C	ISO 75-1/-2
DSC (Melt Point)	280	°C	ISO 11357
Physical Properties			
Density	1660	kg/m³	ISO 1183
Flammability			
Flammability (3.0 mm)	V-0	class	UL 94