

Technical Data Sheet - Preliminary Product

❖ Alfater XL®

MOCOM

ALFATER XL A60I 4GP0000

Base Polymer	Thermoplastic Vulcanisate (PP+EPDM)
Colour	natural color,bright inherent color
Service Temperature	max. range (depending on load, geometry, etc.) -40-125 °C
Special Features	low emission,good colorability,easy flow,good weathering resistance,good chemical resistance,good ozone resistance,good hot air resistance,good hydrolysis resistant
Market Segment	Automotive,building and construction,do-it-yourself,electrical and electronic,sport and leisure,Furniture
Application Area	injection moulded parts
Typical Applications	seals,sealing lip,handles,racking / shelving,soft touch elements,impact protection / shock absorber,protection caps,thin walled parts,profile,cable ducts,casters,2K components
Adhesion to	Polypropylene Homopolymer,Polypropylene Copolymer,Polyethylene,Thermoplastic Vulcanisate (PP+EPDM),Thermoplastic Olefin Elastomer,Thermoplastic Elastomer general,Ethylene propylene diene rubber

Pre-Drying Conditions	in a dry air (dessiccant) dryer 60-70 °C for 2-4 h max. moisture content <0,10 %
Processing Injection Moulding	melt temperature 190-220 °C mould temperature 10-60 °C injection speed middle - high back pressure (hydraulic) >3 bar holding pressure 50-70% of injection pressure
Storage	dry, protected from light not above 30°C tightly sealed do not stack the pallets

Properties	Value	Dimension	Test Norm
Mechanical Properties			
Tensile Stress at 100% Elongation (Type 2)	2.1	MPa	ISO 37
Tensile Strength (Type 2)	5.5	MPa	ISO 37
Tear Strength (Method Ba)	24	kN/m	ISO 34-1
Elongation at Break (Type 2)	500	%	ISO 37
Shore Hardness A (15s)	60	-	ISO 868
Thermal Properties			
Compression Set (22h / 100°C / 25% / Type A)	41	%	ISO 815

Technical Data Sheet - Preliminary Product

❖ Alfater XL[®]

MOCOM

ALFATER XL A60I 4GP0000

Electrical Properties

Tracking Resistance (CTI)	600	-	IEC 60112
---------------------------	-----	---	-----------

Physical Properties

Density	930	kg/m ³	ISO 1183
---------	-----	-------------------	----------

Ageing Properties

Ozone resistance (method A)	passed	-	ISO 1431-1A
-----------------------------	--------	---	-------------